

OIL ANALYSIS REPORT

Sample Rating Trend

Area **RIG** 274 Machine Id **R274-MP-03** Component **Gearbox** Fluid **{not provided} (--- GAL)**

DIAGNOSIS

Recommendation

We recommend you service the filters on this component. We recommend an early resample to monitor this condition. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. The system cleanliness is above the acceptable limit for the target ISO 4406 cleanliness code.

Fluid Condition


The AN level is acceptable for this fluid. The oil is still serviceable provided that the contaminant(s) can be reduced to acceptable levels.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KL0014284	KL0014294	KL0013737
Sample Date		Client Info		06 May 2024	02 Apr 2024	04 Mar 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	ABNORMAL	ABNORMAL
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	9	15	3
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m	>25	3	0	0
Lead	ppm	ASTM D5185m	>50	0	0	0
Copper	ppm	ASTM D5185m	>200	4	3	4
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		<1	<1	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		1	<1	0
Calcium	ppm	ASTM D5185m		26	10	0
Phosphorus	ppm	ASTM D5185m		135	123	107
Zinc	ppm	ASTM D5185m		16	0	0
Sulfur	ppm	ASTM D5185m		9682	9379	8476
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	17	8	6
Sodium	ppm	ASTM D5185m		2	6	1
Potassium	ppm	ASTM D5185m	>20	1	0	0
1 otassiam			200	•	0	
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
	ESS	method ASTM D7647				history2 ▲ 87204
FLUID CLEANLIN Particles >4µm	ESS		limit/base	current	history1	
FLUID CLEANLIN Particles >4μm Particles >6μm	ESS	ASTM D7647	limit/base >20000	current	history1 ▲ 149313	▲ 87204
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm	ESS	ASTM D7647 ASTM D7647	limit/base >20000 >5000 >640	current ▲ 129409 ▲ 30242	history1 ▲ 149313 ▲ 38955	▲ 87204▲ 15794
FLUID CLEANLIN	ESS	ASTM D7647 ASTM D7647 ASTM D7647	limit/base >20000 >5000 >640	current ▲ 129409 ▲ 30242 158	history1 ▲ 149313 ▲ 38955 625 	 87204 15794 303
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm	ESS	ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >20000 >5000 >640 >160 >40	current ▲ 129409 ▲ 30242 158 15	history1 ▲ 149313 ▲ 38955 625 112 	 87204 15794 303 43
FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm	ESS	ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >20000 >5000 >640 >160 >40	current ▲ 129409 ▲ 30242 158 15 0	history1	 87204 15794 303 43 1
FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm Particles >71µm		ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >20000 >5000 >640 >160 >40 >10	current ▲ 129409 ▲ 30242 158 15 0 0 0	history1 ▲ 149313 ▲ 38955 625 112 2 0	 87204 15794 303 43 1 0
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm Particles >71μm Oil Cleanliness		ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ISO 4406 (c)	limit/base >20000 >5000 >640 >160 >40 >10 >10 >21/19/16	current ▲ 129409 ▲ 30242 158 15 0 0 24/22/14	history1	 87204 15794 303 43 1 0 24/21/15


t/Location: RICKY MATA - PATMIDTX Page 1 of 2




OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
	IES cSt	method ASTM D445	limit/base	current 323	history1 325	history2 318
FLUID PROPERT	cSt		limit/base limit/base			
FLUID PROPERT Visc @ 40°C	cSt	ASTM D445		323	325	318



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 **PATTERSON - UTI DRILLING** Sample No. : KL0014284 Received : 16 May 2024 9915 WEST INDUSTRIAL Lab Number : 06181296 Tested : 17 May 2024 MIDLAND, TX Unique Number : 11032622 Diagnosed : 17 May 2024 - Wes Davis US 79706 Test Package : MOB 2 (Additional Tests: PrtCount) Contact: RICKY MATA Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. ricky.mata@patenergy.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (832)219-4559 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (432)561-9388

Report Id: PATMIDTX [WUSCAR] 06181296 (Generated: 05/17/2024 11:32:55) Rev: 1

Contact/Location: RICKY MATA - PATMIDTX

Page 2 of 2