

OIL ANALYSIS REPORT

ISO

Machine Id

HOMO 2 Component Gearbox Fluid GEAR OIL (PAG) ISO 220 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 6 microns in size) present in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP0011855		
Sample Date		Client Info		15 May 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				ATTENTION		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	1		
Chromium	ppm	ASTM D5185m	>15	0		
Nickel	ppm	ASTM D5185m	>15	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>25	<1		
Lead	ppm	ASTM D5185m	>100	0		
Copper	ppm	ASTM D5185m	>200	<1		
Tin	ppm	ASTM D5185m	>25	0		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0		
Barium	ppm	ASTM D5185m	5	0		
Molybdenum	ppm	ASTM D5185m	5	0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m	5	0		
Calcium	ppm	ASTM D5185m	5	<1		
Phosphorus	ppm	ASTM D5185m	775	524		
Zinc	ppm	ASTM D5185m	5	4		
Sulfur	ppm	ASTM D5185m	2000	640		
CONTAMINANTS	\$	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	4		
Sodium	ppm	ASTM D5185m		1		
Potassium	ppm	ASTM D5185m	>20	0		
Water	%	ASTM D6304	>0.2	0.002		
ppm Water	ppm	ASTM D6304	>2000	17		
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	e 21879		
Particles >6µm		ASTM D7647	>5000	1762		
Particles >14µm		ASTM D7647	>640	32		
Particles >21µm		ASTM D7647	>160	5		
Particles >38µm		ASTM D7647	>40	1		
Particles >71µm		ASTM D7647	>10	1		
Oil Cleanliness		ISO 4406 (c)	>21/19/16	e 22/18/12		
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	2.00	0.33		



OIL ANALYSIS REPORT



NONE *Visual NONE scalar *Visual NONE NONE scalar NONE scalar *Visua NONE scalar *Visual NONE NONE *Visual NONE LIGHT scalar NONE NONE scalar *Visual NORML *Visual NORML scalar *Visual NORML NORML scalar *Visual scalar >0.2 NEG *Visual NEG scalar ASTM D445 220 227 no image no image no image no image Particle Count 491.5 122,88 30.72 7,680 (per 1 ml) May15/24 4406 1,920 :1999 Cle es 480 120 14 31 214 28 Acid Number (⁶/H0) 4.00 Ab Ē 3.00 · P 2.00 Acid Nu 1.00 0.00 May15/24 Mav1 Um' : WearCheck USA - 501 Madison Ave., Cary, NC 27513 **KROGER/KING SOOPERS MEAT PLANT** Received : 16 May 2024 65 YUMA ST Tested DENVER, CO : 17 May 2024 Diagnosed : 20 May 2024 - Jonathan Hester US 80223

Contact: DEREK HENKOWSKI derek.henkowski@kingsoopers.com T: (303)778-3029 F: (303)698-3479 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: KRODEN [WUSCAR] 06181358 (Generated: 05/20/2024 11:13:34) Rev: 1

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Contact/Location: DEREK HENKOWSKI - KRODEN