


OIL ANALYSIS REPORT



GAS K-4300A (S/N A AIR COMPRESSOR)

Air Compressor

CHEVRON GST OIL ISO 68 (18 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid. The amount and size of particulates present in the system are acceptable.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the fluid is suitable for further service.


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		HLC0003308	HLC0003212	HLC0003214
Sample Date		Client Info		07 May 2024	01 Apr 2024	08 Mar 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	V	method	limit/base	current	history1	history2
Water		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	<1
Chromium	ppm	ASTM D5185m	>4	0	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	<1	<1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m	>10	0	1	2
Lead	ppm	ASTM D5185m	>20	<1	1	<1
Copper	ppm	ASTM D5185m	>40	<1	<1	<1
Tin	ppm	ASTM D5185m	>5	0	1	<1
Vanadium	ppm	ASTM D5185m		<1	<1	<1
Cadmium	ppm	ASTM D5185m		0	<1	<1
ADDITIVES		method	limit/base	current	history1	history2
	200	ASTM D5185m	mm saco	0	0	0
Boron Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	<1
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium		ASTM D5185m		0	<1	<1
Calcium	ppm	ASTM D5185m		28	4	3
Phosphorus	ppm	ASTM D5185m		9	50	11
Zinc	ppm	ASTM D5185m		0	<1	0
Sulfur	ppm	ASTM D5185m		1000	821	860
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	0	<1
Silicon Sodium	ppm ppm	ASTM D5185m ASTM D5185m	>25	<1 2	0	<1 0
Silicon Sodium Potassium	ppm ppm ppm	ASTM D5185m	>25 >20	<1 2 <1	0 0 1	<1
Silicon Sodium Potassium FLUID CLEANLIN	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method	>25	<1 2 <1 current	0 0 1 history1	<1 0
Silicon Sodium Potassium FLUID CLEANLIN Particles >4µm	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D7647	>25 >20 limit/base	<1 2 <1 current	0 0 1 history1	<1 0 1
Silicon Sodium Potassium FLUID CLEANLIN Particles >4µm Particles >6µm	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D7647 ASTM D7647	>25 >20 limit/base >2500	<1 2 <1 current 43 17	0 0 1 history1 390 63	<1 0 1 history2
Silicon Sodium Potassium FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D7647 ASTM D7647 ASTM D7647	>25 >20 limit/base >2500 >320	<1 2 <1 current 43 17 1	0 0 1 history1 390 63 4	<1 0 1 history2
Silicon Sodium Potassium FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>25 >20 limit/base >2500 >320 >80	<1 2 <1 current 43 17 1 1	0 0 1 history1 390 63 4	<1 0 1 history2
Silicon Sodium Potassium FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>25 >20 limit/base >2500 >320 >80 >20	<1 2 <1 current 43 17 1 1 0	0 0 1 history1 390 63 4 1	<1 0 1 history2
Silicon Sodium Potassium FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm Particles >71µm	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>25 >20 limit/base >2500 >3200 >320 >80 >20 >4	<1 2 <1 current 43 17 1 1 0 0 0	0 0 1 history1 390 63 4 1 0	<1 0 1 history2
Silicon Sodium Potassium FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>25 >20 limit/base >2500 >320 >80 >20	<1 2 <1 current 43 17 1 1 0	0 0 1 history1 390 63 4 1	<1 0 1 history2





OIL ANALYSIS REPORT

SAMPLE IMAGES










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.6	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	method	limit/base	current	history1	history2	
PLUID PHOPEN I	TES	method			HISTOLAL	History∠

Visc @ 40°C	cSt	ASTM D445	64.6	68.6	68.6	68.7

Color **Bottom**







Certificate 12367

Laboratory

Sample No.

: HLC0003308 Lab Number : 06181977 Unique Number : 11033303

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 16 May 2024 **Tested**

Diagnosed

: 20 May 2024 : 20 May 2024 - Don Baldridge Test Package : IND 2 (Additional Tests: PrtCount)

PRUDHOE BAY, AK US 99734 Contact: PERRY NEEL pneel@hilcorp.com T: (907)670-3514 F: (907)659-5377

HILCORP NORTHSTAR FACILITY

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) Report Id: BPENOR [WUSCAR] 06181977 (Generated: 05/20/2024 12:46:09) Rev: 1

Contact/Location: PERRY NEEL - BPENOR