

# **OIL ANALYSIS REPORT**

# Area Store 8 - Pikeville PRIME TECH PT-175 PT-175-00870

Hydraulic System

PAKELO HYDROSYNT P ISO 46 (--- GAL)

## DIAGNOSIS

#### Recommendation

We advise that you perform a filter service, and use off-line filtration to improve the cleanliness of the system fluid. We recommend an early resample to monitor this condition.

## Wear


All component wear rates are normal.

### Contamination

There is a moderate amount of particulates (2 to 100 microns in size) present in the oil.

#### Fluid Condition

The AN level is acceptable for this fluid. The oil is still serviceable provided that the contaminant(s) can be reduced to acceptable levels.



SAMPLE INFORM	IATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		LEC0046371			
Sample Date		Client Info		14 May 2024			
Machine Age	hrs	Client Info		234			
Oil Age	hrs	Client Info		234			
Oil Changed		Client Info		Not Changd			
Sample Status				ABNORMAL			
CONTAMINATION		method	limit/base	current	history1	history2	
Water		WC Method	>0.1	NEG			
WEAR METALS		method	limit/base	current	history1	history2	
PQ		ASTM D8184		17			
Iron	ppm	ASTM D5185m	>20	5			
Chromium	ppm	ASTM D5185m	>10	<1			
Nickel	ppm	ASTM D5185m	>10	0			
Titanium	ppm	ASTM D5185m		<1			
Silver	ppm	ASTM D5185m		<1			
Aluminum	ppm	ASTM D5185m	>10	<1			
Lead	ppm	ASTM D5185m	>10	<1			
Copper	ppm	ASTM D5185m	>75	3			
Tin	ppm	ASTM D5185m	>10	<1			
Vanadium	ppm	ASTM D5185m		0			
Cadmium	ppm	ASTM D5185m		<1			
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		0			
Barium	ppm	ASTM D5185m		0			
Molybdenum	ppm	ASTM D5185m		0			
Manganese	ppm	ASTM D5185m		<1			
Magnesium	ppm						
	ppin	ASTM D5185m		0			
Calcium	ppm	ASTM D5185m ASTM D5185m		0 58			
U U				-			
Calcium	ppm	ASTM D5185m		58			
Calcium Phosphorus	ppm ppm	ASTM D5185m ASTM D5185m		58 383			
Calcium Phosphorus Zinc	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	limit/base	58 383 460			
Calcium Phosphorus Zinc Sulfur	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m		58 383 460 1366			
Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method		58 383 460 1366 current			
Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m <b>method</b> ASTM D5185m		58 383 460 1366 current 1	   history1	   history2	
Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium	ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>20	58 383 460 1366 <u>current</u> 1 <1	   history1	  history2 	
Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium	ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m Method ASTM D5185m ASTM D5185m	>20 >20	58 383 460 1366 <u>current</u> 1 <1 0	  history1 	  history2  	
Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium FLUID CLEANLIN	ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>20 >20 limit/base	58 383 460 1366 current 1 <1 <1 0 current	  history1   history1	  history2   history2	

ASTM D7647 >40

ASTM D7647 >10

ASTM D7647 >3

Particles >21µm

Particles >38µm

Particles >71µm

**Oil Cleanliness** 

85

3

1

ISO 4406 (c) >19/17/14 A 22/19/15



# **OIL ANALYSIS REPORT**

Acid Number (AN) VISUAL White Metal Yellow Metal Precipitate Silt Debris Sand/Dirt Appearance Odor Emulsified Water Free Water FLUID PROPER	mg KOH/g scalar scalar scalar scalar scalar scalar scalar scalar scalar	method *Visual *Visual *Visual *Visual *Visual *Visual *Visual	limit/base NONE NONE NONE NONE NONE NONE	0.52 current NONE NONE LIGHT NONE NONE	 history1   	 history2   
White Metal Yellow Metal Precipitate Silt Debris Sand/Dirt Appearance Odor Emulsified Water Free Water	scalar scalar scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual *Visual *Visual *Visual	NONE NONE NONE NONE NONE	NONE NONE NONE LIGHT NONE		
White Metal Yellow Metal Precipitate Silt Debris Sand/Dirt Appearance Odor Emulsified Water Free Water	scalar scalar scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual *Visual *Visual	NONE NONE NONE NONE	NONE NONE LIGHT NONE		
Yellow Metal Precipitate Silt Debris Sand/Dirt Appearance Odor Emulsified Water Free Water	scalar scalar scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual *Visual *Visual	NONE NONE NONE NONE	NONE NONE LIGHT NONE		
Precipitate Silt Debris Sand/Dirt Appearance Odor Emulsified Water Free Water	scalar scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual	NONE NONE NONE	LIGHT NONE		
Silt Debris Sand/Dirt Appearance Odor Emulsified Water Free Water	scalar scalar scalar scalar	*Visual *Visual *Visual	NONE NONE	NONE		
Sand/Dirt Appearance Odor Emulsified Water Free Water	scalar scalar scalar	*Visual *Visual	NONE			
Appearance Odor Emulsified Water Free Water	scalar scalar	*Visual		NONE		
Odor Emulsified Water Free Water	scalar					
Emulsified Water Free Water			NORML	NORML		
Free Water	Scalar	*Visual	NORML	NORML		
		*Visual	>0.1	NEG		
FLUID PROPERT	scalar	*Visual		NEG		
	<b>FIES</b>	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		42.5		
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
May						
Color					no image	no image
					no inago	no imago
			1			
Bottom					no image	no image
GRAPHS						
Ferrous Alloys			100 APR	Particle Count		_2
2 iron						
E. 5-				Severe		-2
			30,720	1		-2
24 0 24			47,680	Abnormal		+2 -1 -1 -1
May14			ber 1.920-		•	-1
Non-ferrous Meta	s					
10 copper			្រ ឆ្នាំ 120-			-1
E. 5.			4m 30-			-1
2 0 <b>1</b>						
ay14/2			ay14/2			
≥ Viscosity @ 40°C			≥ 0.4	μ 6μ	14µ 21µ	38µ 71µ
55 T			<sup>®</sup> 0.60-	Acid Number		
			20.40			
45						
			N N N N N N N N N N N N N N N N N N N			
4/24				4/24		
Mayl			May1	May14/2		
	Color Bottom GRAPHS Ferrous Alloys	Color Bottom GRAPHS Ferrous Alloys Non-ferrous Metals Viscosity @ 40°C	Color Bottom GRAPHS Ferrous Alloys Non-ferrous Metals Viscosity @ 40°C	Color Bottom GRAPHS Ferrous Alloys	Color Bottom GRAPHS Ferrous Alloys	Color no image Bottom Particle Count GRAPHS Ferrous Alloys Viscosity @ 40°C Copper down Copper down Co

Report Id: LESMAROH [WUSCAR] 06182715 (Generated: 05/22/2024 06:41:08) Rev: 2

Contact/Location: STORE 9 - MARIETTA - LEANNE KENDALL - LESMAROH