




OIL ANALYSIS REPORT



Machine Id
Pinconning CAT 1 PINM01BE
 Component
Biogas Engine
 Fluid
CHEVRON HDAX 9500 GAS ENGINE OIL 40 (--- GAL)

Sample Rating Trend



NORMAL

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0840744	WC0840735	WC0840763
Sample Date	Client Info		15 May 2024	07 May 2024	26 Apr 2024
Machine Age	hrs	Client Info	66966	66775	66512
Oil Age	hrs	Client Info	637	446	183
Oil Changed	Client Info		Not Chngd	Not Chngd	Not Chngd
Sample Status			NORMAL	ABNORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>4.0	<1.0	<1.0	<1.0
Water	WC Method		NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >14	0	4	<1
Chromium	ppm	ASTM D5185m >3	0	<1	0
Nickel	ppm	ASTM D5185m	0	<1	0
Titanium	ppm	ASTM D5185m	0	<1	0
Silver	ppm	ASTM D5185m	0	0	0
Aluminum	ppm	ASTM D5185m >5	2	2	1
Lead	ppm	ASTM D5185m >8	<1	1	<1
Copper	ppm	ASTM D5185m >5	1	2	<1
Tin	ppm	ASTM D5185m >3	1	▲ 3	0
Vanadium	ppm	ASTM D5185m	0	<1	0
Cadmium	ppm	ASTM D5185m	0	<1	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	19	75	19
Barium	ppm	ASTM D5185m	0	0	0
Molybdenum	ppm	ASTM D5185m	4	9	4
Manganese	ppm	ASTM D5185m	<1	<1	0
Magnesium	ppm	ASTM D5185m	3	59	22
Calcium	ppm	ASTM D5185m	1658	1501	1618
Phosphorus	ppm	ASTM D5185m	285	422	295
Zinc	ppm	ASTM D5185m	363	577	358
Sulfur	ppm	ASTM D5185m	2296	3721	2406

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >180	115	▲ 196	56
Sodium	ppm	ASTM D5185m >20	1	0	<1
Potassium	ppm	ASTM D5185m >20	<1	2	<1

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	0	0	0
Nitration	Abs/cm	*ASTM D7624	5.4	3.4	4.7
Sulfation	Abs/.1mm	*ASTM D7415	18.1	17.1	15.5


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	11.6	9.5	8.5
Acid Number (AN)	mg KOH/g	ASTM D8045 1.0	1.03	0.60	0.61
Base Number (BN)	mg KOH/g	ASTM D2896 5.4	3.88	4.94	4.29




OIL ANALYSIS REPORT


FT-IR (Direct Trend)




Acid Number



Base Number











Viscosity @ 100°C



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	NEG	NEG	NEG
Free Water	scalar	*Visual	NEG	NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	13.4	13.6	13.9	13.3

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : WC0840744

Lab Number : 06183053

Unique Number : 11034379

Test Package : MOB 2

Received : 17 May 2024

Tested : 20 May 2024

Diagnosed : 20 May 2024 - Sean Felton

EDL NA Recips-Pinconning

Pinconning Powerstation, 2403 E. Whitefeather Road

Pinconning, MI

US 48650

Contact: DOUG HINE

doug.hine@edlenergy.com

T:

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)