

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area ACS-46 [418940] ATLAS COPCO AIF074060R - SILGAN

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06183377		
Sample Date		Client Info		16 May 2024		
Machine Age	hrs	Client Info		15649		
Oil Age	hrs	Client Info		1653		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	٧	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1		
Chromium	ppm	ASTM D5185m	>5	<1		
Nickel	ppm	ASTM D5185m		<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>15	2		
Lead	ppm	ASTM D5185m	>65	<1		
Copper	ppm	ASTM D5185m	>65	1		
Tin	ppm	ASTM D5185m	>10	1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0.0	0		
Barium	ppm	ASTM D5185m	0.0	0		
Molybdenum	ppm	ASTM D5185m	0	<1		
Manganese	ppm	ASTM D5185m	0	<1		
Magnesium	ppm	ASTM D5185m	0.0	<1		
Calcium	ppm	ASTM D5185m	0.0	4		
Phosphorus	ppm	ASTM D5185m	966	204		
Zinc	ppm	ASTM D5185m	0	<1		
Sulfur	ppm	ASTM D5185m	1309	512		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	3		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	2		
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.172	0.25		



OIL ANALYSIS REPORT

VISUAI



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
6/24 -	Appearance	scalar	*Visual	NORML	NORML		
May16/24	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
	Free Water	scalar	*Visual		NEG		
				11 11 11			
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	39.9	44.5		
	SAMPLE IMAGES	S	method	limit/base	current	history1	history2
May16/24	Color				a.	no image	no image
	Bottom					no image	no image
	Non-ferrous Metal			May16/24			
	Non-ferrous Metal			May16/24 May16/24	Acid Number		
	Non-ferrous Metal			May16/24 May16/24			
	Non-ferrous Metal			May16/24 May16/24			
	Non-ferrous Metal			May16/24 May16/24			
	Non-ferrous Metal			May16/24 May16/24			
	Non-ferrous Metal			May16/24 May16/24 May16/24 May16/24	Base		
	Non-ferrous Metal			May16/24 10.00 11.00 11.00 11.00 11.00 10.01 10.01 10.02 10.	Base		

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: ELVIN DIAZ - UCAIRCAR

F: (201)342-6241