

## **OIL ANALYSIS REPORT**

### Area **ATLAS COPCO ITJ154080 - BRICK PUBLIC WORKS** Component Compressor

#### Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

#### Wear


All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend




NORMAL

SAMPLE INFORM	NATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06183385		
Sample Date		Client Info		16 May 2024		
Machine Age	hrs	Client Info		6149		
Oil Age	hrs	Client Info		617		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1		
Chromium	ppm	ASTM D5185m	>5	<1		
Nickel	ppm	ASTM D5185m		<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>15	2		
Lead	ppm	ASTM D5185m	>65	<1		
Copper	ppm	ASTM D5185m	>65	3		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		1		
Calcium	ppm	ASTM D5185m		4		
Phosphorus	ppm	ASTM D5185m		79		
Zinc	ppm	ASTM D5185m		182		
Sulfur	ppm	ASTM D5185m		135		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	2		
Sodium	ppm	ASTM D5185m		3		
Potassium	ppm	ASTM D5185m	>20	1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.26		



# **OIL ANALYSIS REPORT**



			method	limit/base		history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
5/24	Appearance	scalar	*Visual	NORML	NORML		
May16/24	Odor	scalar	*Visual	NORML	NORML		
E	Emulsified Water	scalar	*Visual	>0.1	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		47.4		
	SAMPLE IMAGES	5	method	limit/base	current	history1	history2
May16/24 -	Color					no image	no image
	Bottom					no image	no image
	2 10 10 10 10 10 10 10 10 10 10			May16/24			
	udd 2 tin tin to be tin to be tin to be to be to to			May16/24	Acid Number		
	ead tin 2 0 T Viscosity @ 40°C 55 Abnomal			May16/24 +			
	Viscosity @ 40°C			May16/24 +			
	Viscosity @ 40°C			May16/24 +			
	Viscosity @ 40°C			May16/24 +			
	Viscosity @ 40°C			(0,0.30 (0,0.10,0.24 ) 0.110 (0,0.10,0.24 ) 0.0.12 (0,0.10,0.24 ) 0.0.12 (0,0.10,0.24)			
	Viscosity @ 40°C			60.030 (0) KOM (0) KOM (0) KOM (0) KOM (0) C24 (0) C24			
	Viscosity @ 40°C			(0,0.30 (0,0.10,0.24 ) 0.110 (0,0.10,0.24 ) 0.0.12 (0,0.10,0.24 ) 0.0.12 (0,0.10,0.24)			

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: UCAIRCAR [WUSCAR] 06183385 (Generated: 05/20/2024 19:29:56) Rev: 1

Contact/Location: ELVIN DIAZ - UCAIRCAR

F: (201)342-6241