


OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

BACON MIXER - RED (S/N 10064269)

Component **Gearbox**

PETRO CANADA PURITY FG EP GEAR FLUID 460 (--- GAL)

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

Appearance is hazy. There is no indication of any contamination in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		WC0773911	WC0794759	WC0667253	
Sample Date		Client Info		20 Apr 2024	30 Nov 2023	04 Apr 2023	
Machine Age	mths	Client Info		0	0	0	
Oil Age	mths	Client Info		0	0	0	
Oil Changed		Client Info		N/A	N/A	N/A	
Sample Status				ATTENTION	NORMAL	NORMAL	
CONTAMINATION		method	limit/base	current	history1	history2	
Water		WC Method	>0.2	NEG	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2	
PQ		ASTM D8184		35	53	12	
Iron	ppm	ASTM D5185m	>200	38	24	20	
Chromium	ppm	ASTM D5185m	>15	<1	0	0	
Nickel	ppm	ASTM D5185m	>15	<1	0	0	
Titanium	ppm	ASTM D5185m		2	0	<1	
Silver	ppm	ASTM D5185m		<1	0	0	
Aluminum	ppm	ASTM D5185m	>25	2	0	<1	
Lead	ppm	ASTM D5185m	>100	<1	0	0	
Copper	ppm	ASTM D5185m	>200	<1	0	0	
Tin	ppm	ASTM D5185m	>25	<1	0	0	
Vanadium	ppm	ASTM D5185m		<1	0	0	
Cadmium	ppm	ASTM D5185m		<1	0	0	
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		0	0	0	
Barium	ppm	ASTM D5185m		0	0	0	
Molybdenum	ppm	ASTM D5185m		<1	0	0	
Manganese	ppm	ASTM D5185m		<1	0	0	
Magnesium	ppm	ASTM D5185m		<1	0	4	
Calcium	ppm	ASTM D5185m		4	0	0	
Phosphorus	ppm	ASTM D5185m	135	189	140	172	
Zinc	ppm	ASTM D5185m	222	3	0	9	
Sulfur	ppm	ASTM D5185m	660	798	667	864	
CONTAMINANTS	3	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>50	7	4	4	
Sodium	ppm	ASTM D5185m		0	0	<1	
Potassium	ppm	ASTM D5185m	>20	2	0	0	
FLUID DEGRADA	NOITA	method	limit/base	current	history1	history2	
Acid Number (AN)	mg KOH/g	ASTM D8045	0.54	0.34	0.28	0.37	



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	LIGHT
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	HAZY	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	460	429	416	423

	ш.	A	03					4
	ь.							
25/	PQ							
250	, I							
	Smuore							
200	Severe					-		
150	0							
P								
100	Abnom	nal						
100	1							
50	0+					-	/	
				_				
(ل			_	$\overline{}$	_	-	_
	g31/19	20	721	/21	22	23	23	2,0
	31	ar29/7	Sep7	7.00	ct10/	4	30/	5
		는 등	Š	ž	5	Ā	2	ì

SAMPLE IMAGES Color

Bottom

GRAPHS Ferrous Alloys PQ 220 160 140 2 120 · 100 Non-ferrous Metals 80 60 40 Viscosity @ 40°C Acid Number 550 (B_{0.60} (B_HO.48 500 (2-04) 450 450 Ē 0.36 0.24 0.12 400 Acid 7 350 Nov7/21.





Laboratory Sample No.

: WC0773911 Lab Number : 06183409 Unique Number : 11034735

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 17 May 2024 **Tested** Diagnosed

: 20 May 2024 : 21 May 2024 - Don Baldridge **WORTHINGTON FOODS INC** 1675 FAIRVIEW ROAD ZANESVILLE, OH

US 43701-5168 Contact: Service Manager

Test Package : IND 2 (Additional Tests: PQ) Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: WORZAN [WUSCAR] 06183409 (Generated: 05/21/2024 19:21:03) Rev: 1

Submitted By: Cecil Richards

T:

F: