




# OIL ANALYSIS REPORT

Sample Rating Trend



GLYCOL



Area  
**[23091]**

Machine Id

**20-66**

Component

**Diesel Engine**

Fluid

**CONOCO PHILLIPS GUARDOL ECT 15W40 (--- GAL)**

## DIAGNOSIS

### ▲ Recommendation

Check for low coolant level. We advise that you check for the source of the coolant leak. Oil and filter change at the time of sampling has been noted. We recommend an early resample to monitor this condition.

### Wear

All component wear rates are normal.

### ▲ Contamination

Sodium and/or potassium levels are high.

### ▲ Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>WC0923368</b>	WC0548946	---
Sample Date	Client Info		<b>30 Apr 2024</b>	11 May 2021	---
Machine Age	hrs	Client Info	<b>7777</b>	2763	---
Oil Age	hrs	Client Info	<b>500</b>	263	---
Oil Changed	Client Info		<b>Changed</b>	Changed	---
Sample Status			<b>ABNORMAL</b>	NORMAL	---

## CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<b>&lt;1.0</b>	<1.0	---
Water	WC Method	>0.2	<b>NEG</b>	NEG	---

## WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>100	<b>23</b>	4	---
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	<1	---
Nickel	ppm	ASTM D5185m	>4	<b>0</b>	<1	---
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	---
Silver	ppm	ASTM D5185m	>3	<b>0</b>	<1	---
Aluminum	ppm	ASTM D5185m	>20	<b>10</b>	3	---
Lead	ppm	ASTM D5185m	>40	<b>6</b>	<1	---
Copper	ppm	ASTM D5185m	>330	<b>64</b>	<1	---
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	<1	---
Antimony	ppm	ASTM D5185m		<b>---</b>	0	---
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	---
Cadmium	ppm	ASTM D5185m		<b>0</b>	0	---

## ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	85	<b>71</b>	93	---
Barium	ppm	ASTM D5185m		<b>0</b>	0	---
Molybdenum	ppm	ASTM D5185m		<b>11</b>	18	---
Manganese	ppm	ASTM D5185m		<b>1</b>	<1	---
Magnesium	ppm	ASTM D5185m	350	<b>759</b>	627	---
Calcium	ppm	ASTM D5185m	1800	<b>1377</b>	1458	---
Phosphorus	ppm	ASTM D5185m	1000	<b>1135</b>	1060	---
Zinc	ppm	ASTM D5185m	1100	<b>1255</b>	1139	---
Sulfur	ppm	ASTM D5185m	3500	<b>4463</b>	3282	---

## CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>25	<b>6</b>	2	---
Sodium	ppm	ASTM D5185m		<b>▲ 72</b>	21	---
Potassium	ppm	ASTM D5185m	>20	<b>▲ 137</b>	33	---
Glycol	%	*ASTM D2982		<b>NEG</b>	NEG	---

## INFRA-RED





	method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844	>3	<b>0.1</b>	0.1	---
Nitration	Abs/cm	*ASTM D7624	>20	<b>6.9</b>	6.8	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>19.5</b>	20.4	---

## FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>14.0</b>	14.1	---
Base Number (BN)	mg KOH/g	ASTM D2896	9.5	<b>8.4</b>	10.2	---







# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.3	<b>13.8</b>	14.0	---

### GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : WC0923368      **Received** : 17 May 2024  
**Lab Number** : **06183616**      **Tested** : 21 May 2024  
**Unique Number** : 11034942      **Diagnosed** : 21 May 2024 - Sean Felton  
**Test Package** : CONST ( Additional Tests: Glycol, TBN )

**MANHATTAN ROAD AND BRIDGE**  
 5601 S 122ND E AVE  
 TULSA, OK  
 US 74146  
 Contact: BEN CALDWELL  
 kevin.marson@wearcheck.com  
 T: (918)728-5749  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)