

## **OIL ANALYSIS REPORT**

Sample Rating Trend

### NORMAL

Machine Id

# JOHN DEERE 50G 1FF050GXCLH293048

Diesel Engine

Fluid JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (9 GAL)

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		JR0212159	JR0182157	JR0153427
Sample Date		Client Info		16 May 2024	10 Aug 2023	28 Nov 2022
Machine Age	hrs	Client Info		1716	1432	985
Oil Age	hrs	Client Info		500	447	985
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>51	7	11	19
Chromium	ppm	ASTM D5185m	>11	0	0	<1
Nickel	ppm	ASTM D5185m	>5	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	<1	0
Aluminum	ppm	ASTM D5185m	>31	3	3	4
Lead	ppm	ASTM D5185m	>26	<1	2	3
Copper	ppm	ASTM D5185m	>26	0	<1	2
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		286	251	212
Barium	ppm	ASTM D5185m		<1	3	0
Molybdenum	ppm	ASTM D5185m		226	270	229
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		757	793	711
Calcium	ppm	ASTM D5185m		1353	1473	1499
Phosphorus	ppm	ASTM D5185m		850	910	738
Zinc	ppm	ASTM D5185m		1016	1119	990
Sulfur	ppm	ASTM D5185m		3349	3156	3013
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>22	10	11	15
Sodium	ppm	ASTM D5185m	>31	<1	0	3
Potassium	ppm	ASTM D5185m	>20	<1	3	21
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.2	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	8.2	9.1	9.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.5	22.2	26.9
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.1	18.3	25.3
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.4	9.0	7.0
5:56:17) Bev: 1		Submitted By: TECHNICIAN ACCOUNT				

Report Id: JAMASH [WUSCAR] 06184091 (Generated: 05/22/2024 05:56:17) Rev: 1


Submitted By: TECHNICIAN ACCOUNT




# **OIL ANALYSIS REPORT**



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	14.2	12.5
GRAPHS						





Submitted By: TECHNICIAN ACCOUNT