

OIL ANALYSIS REPORT

Area **Refrigeration Compressor VILTER TYSCJ 4VILT**

Refrigeration Compressor USPI 1009-68 SC (--- QTS)

DIAGNOSIS

A Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP0011750	USP0007589	USP0003595
Sample Date		Client Info		14 May 2024	27 Feb 2024	14 Nov 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	1	10	3
Chromium	ppm	ASTM D5185m	>2	0	0	<1
Nickel	ppm	ASTM D5185m		0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	0	0	0
Lead	ppm	ASTM D5185m	>2	0	0	0
Copper	ppm	ASTM D5185m		0	0	<1
Tin	ppm	ASTM D5185m	>4	0	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	<1
ADDITIVES	ppin	method	limit/base	current	history1	history2
			in in base			
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	<1
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		<1	0	<1
Calcium	ppm	ASTM D5185m		0	0	0
Phosphorus	ppm	ASTM D5185m		0	0	1
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m	50	0	16	0
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1	0	<1
Sodium	ppm	ASTM D5185m		0	0	0
Potassium	ppm	ASTM D5185m	>20	0	0	1
Water	%	ASTM D6304	>0.01	0.002	0.003	0.001
ppm Water	ppm	ASTM D6304	>100	24	37	0.00
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		42367	714	1565
Particles >6µm		ASTM D7647	>2500	<u> </u>	117	302
Particles >14µm		ASTM D7647	>320	288	5	10
Particles >21µm		ASTM D7647	>80	34	1	1
Particles >38µm		ASTM D7647	>20	0	0	0
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>/18/15	<u> </u>	17/14/10	18/15/10
FLUID DEGRADA	TION	method	limit/base	current	history1	history2

mg KOH/g ASTM D974 0.005

Acid Number (AN)


Contact/Location: THOMAS SCHREIBER - IBPCOL01 Page 1 of 2


0.014


0.015


0.013


















Bottom




: 20 May 2024

: 21 May 2024

: 22 May 2024 - Jonathan Hester





Test Package : IND 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

: USP0011750

: 06184337

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (319)753-6235

Received

Diagnosed

Tested

Report Id: IBPCOL01 [WUSCAR] 06184337 (Generated: 05/22/2024 17:25:09) Rev: 1

Contact/Location: THOMAS SCHREIBER - IBPCOL01

US 52738

T:

HWY 70 North, P.O. Box 272

Contact: THOMAS SCHREIBER

thomas.schreiber@tyson.com

Columbus Junction, IA