

# **OIL ANALYSIS REPORT**

Sample Rating Trend



## Area SW Machine Id SW 300R AGITATOR Component Gearbox

# Fluid GEAR OIL ISO 150 (--- GAL)

### DIAGNOSIS

## Recommendation

Resample at the next service interval to monitor.

## Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

# Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0884850		
Sample Date		Client Info		03 Dec 2023		
Machine Age	yrs	Client Info		0		
Oil Age	yrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	48		
Chromium	ppm	ASTM D5185m	>15	<1		
Nickel	ppm	ASTM D5185m	>15	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>100	<1		
Copper	ppm	ASTM D5185m	>200	<1		
Tin	ppm	ASTM D5185m	>25	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	0		
Barium	ppm	ASTM D5185m	15	<1		
Molybdenum	ppm	ASTM D5185m	15	<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	50	<1		
Calcium	ppm	ASTM D5185m	50	15		
Phosphorus	ppm	ASTM D5185m	350	220		
Zinc	ppm	ASTM D5185m	100	23		
Sulfur	ppm	ASTM D5185m	12500	8775		
CONTAMINANTS	8	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	3		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	6		
FLUID DEGRAD	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.85	0.21		




140

130 Dec3/23 -

Abnormal

# **OIL ANALYSIS REPORT**



	VISUAL		method	limit/base	e current	history1	history2	
	White Metal	scalar	*Visual	NONE	NONE			
	Yellow Metal	scalar	*Visual	NONE	NONE			
	Precipitate	scalar	*Visual	NONE	NONE			
	Silt	scalar	*Visual	NONE	NONE			
	Debris	scalar	*Visual	NONE	LIGHT			
	Sand/Dirt	scalar	*Visual	NONE	NONE			
Dec3/23	Appearance	scalar	*Visual	NORML	NORML			
	Odor Emulsified Water	scalar scalar	*Visual *Visual	NORML >0.2	NORML NEG			
	Free Water	scalar	*Visual	>0.2	NEG			
	FLUID PROPERT		method	limit/base		history1	history2	
	Visc @ 40°C	cSt	ASTM D445	150	144			
	SAMPLE IMAGES		method	limit/base		history1	history2	
- Dec3/23	Color					no image	no image	
	Bottom					no image	no image	
	Non-ferrous Metal:	s		Dec3/23				
	Viscosity @ 40°C			Dec3/23	Acid Number			
	180 Abnormal			(B) <sup>2</sup>				
	170 - 9 ♀ 160			Acid Number (mg K0H/g)	.50 - Abnormal			
	(20160 - 83 150 - <b>Base</b>			ц. 1. 1.	.00 - Base			
	140 - Abnormal				.50 - Abnormal			
	130				.00			
	Dec3/23			Dec3/23	Dec3/23			
unique Number Test Package	: WC0884850 : <mark>06184507</mark> : 11035833	Rece Teste Diagr	Madison Ave., Cary, NC 27513 <b>Received</b> : 20 May 2024 <b>Tested</b> : 21 May 2024 <b>Diagnosed</b> : 22 May 2024 - Jonathan Hester e at 1-800-237-1369. 25 scope of accreditation.			SOLVAY SPARTANBURG 399 SIMS CHAPEL RI SPARTANBURG, SC US 2930 Contact: GREG BLACI gregory.black@syensqo.cor		

Contact/Location: GREG BLACK - SOLSPA