

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

Dutchess county pine plains A050739882/spec b Diesel Engine

Fluid DIESEL ENGINE OIL SAE 15W40 (3 GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0921726	WC0799947	WC0651441
Sample Date		Client Info		20 May 2024	02 May 2023	22 Apr 2022
Machine Age	hrs	Client Info		0	0	968
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	1.9	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	2	2	2
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	2	1	<1
Lead	ppm	ASTM D5185m	>40	1	0	<1
Copper	ppm	ASTM D5185m	>330	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	<1	0	<1
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	250	11	12	7
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	63	45	55
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	450	855	647	847
Calcium	ppm	ASTM D5185m	3000	1194	1430	1037
Phosphorus	ppm	ASTM D5185m	1150	1125	1034	991
Zinc	ppm	ASTM D5185m	1350	1209	1257	1167
Sulfur	ppm	ASTM D5185m	4250	3454	3887	2635
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	2	4
Sodium	ppm	ASTM D5185m	>158	2	<1	2
Potassium	ppm	ASTM D5185m	>20	2	<1	6
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0	0.1
Nitration	Abs/cm	*ASTM D7624	>20	11.0	4.8	5.5
	Abs/cm Abs/.1mm	*ASTM D7624 *ASTM D7415	>20	11.0 23.1	4.8	5.5 19.6
Nitration	Abs/.1mm					
Nitration Sulfation FLUID DEGRADA	Abs/.1mm	*ASTM D7415 method	>30 limit/base	23.1 current	14.7 history1	19.6 history2
Nitration Sulfation FLUID DEGRADA Oxidation	Abs/.1mm . TION Abs/.1mm	*ASTM D7415 method *ASTM D7414	>30 limit/base >25	23.1 current 22.6	14.7 history1 11.5	19.6 history2 14.6
Nitration Sulfation FLUID DEGRADA	Abs/.1mm	*ASTM D7415 method	>30 limit/base	23.1 current 22.6 7.6	14.7 history1 11.5 7.7	19.6 history2


Report Id: GENNEW [WUSCAR] 06185564 (Generated: 05/22/2024 05:55:37) Rev: 1


Page 1 of 2



2.0

OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	hist	ory1		histor	y2
White Metal	scalar	*Visual	NONE	NONE	NON	E	Γ	IONE	
Yellow Metal	scalar	*Visual	NONE NONE NONE		E	NONE			
Precipitate	scalar	*Visual	visual NONE NONE		NON	NONE		NONE	
Silt	scalar	*Visual	al NONE NONE		NONE		NONE		
Debris	scalar	*Visual	-		NON	NONE		NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NON	NONE		NONE	
Appearance	scalar	*Visual	NORML NORML		NORML		NORML		L
Odor	scalar	*Visual	NORML NORML		NORML		NORML		L
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG		NEG		
Free Water	scalar	*Visual		NEG	NEG		NEG		
FLUID PROPERT	IES	method	limit/base	current	hist	ory1		histor	y2
Visc @ 100°C	cSt	ASTM D445	14.4	13.3	12.1		1	12.6	
GRAPHS									
Iron (ppm)			100	Lead (ppm)					
Severe			80	Severe					
			60						
- Abnormal		·····	40	Abnormal					
			20						
			0						_
Apr29/16 May22/17 May14/19	Apr29/21	Apr22/22 May2/23	May20/24	Apr29/16 May22/17 May14/19	Apr26/20	Apr29/21	Apr22/22	May2/23	ACIOCIMIN
Aprá May'	Apr	Apri	Mayi	Aprá Mayi Mayi	Apri	Apr	Aprá	Mar	Mari
Aluminum (ppm)				Chromium (p	pm)				
Severe			50	Severe					
	1 I	I I	40		1	1		1	
Abnormal			³⁰ 20	Abnormal					
				- o ^{minina}					
			10						
19	21	22	24	716	20	/21	22	23	74
Apr29/16 May22/17 May14/19	Apr29/21	Apr22/22 May2/23	May20/24	Apr29/16 May22/17 May14/19	Apr26/20	Apr29/21	Apr22/22	May2/23	₽C/UC/~W
Copper (ppm)		4 1	Z	Silicon (ppm)	4		4		N
T Severe			80	Silicon (ppin)					
Abiroimat			60		1		1	1	
			틆 40	Abnormal					
			20						
			0				_		_
Apr29/16 May22/17 May14/19	Apr29/21	Apr22/22 May2/23	May20/24	Apr29/16 May22/17 May14/19	Apr26/20	Apr29/21	Apr22/22	May2/23	1000 m
Apri May May	Apr	Apri Mar	Mayi	Apri May May	Apri	Apr	Apri	Ma	Man
Viscosity @ 100°C				Base Number					
Abnormal			15.0 \$	Abnormal					
			0.0 mg K0H/g)						
Base	~		E 10.0	Base	1	1	1	-	
Abnormal			gung 5.0	Abnormal					
			ase						
11 17	51	3	0.0			21	12	2	
0	Apr29/21	Apr22/22 May2/23	May20/24	Apr29/16 May22/17 May14/19	Apr26/20	Apr29/21	Apr22/22	May2/23	VC/UC/~W
Apr29/16 May22/17 May14/19			2	2 2 2	Num	-			

: 22 May 2024



Certificate 12367

Unique Number : 11036890 : 22 May 2024 - Wes Davis Diagnosed Test Package : MOB 1 (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Tested

Report Id: GENNEW [WUSCAR] 06185564 (Generated: 05/22/2024 05:55:38) Rev: 1

Laboratory

Sample No.

Lab Number : 06185564

Submitted By: CHRIS HALVORSEN

Page 2 of 2