

OIL ANALYSIS REPORT

Sample Rating Trend





VOLVO A35G 342019

Component Bogie/Center Axle

Fluid VOLVO SUPER GEAR OIL 75W-80-GO102 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

| SAMPLE INFORM | IATION | method | limit/base | current | history1 | history2 |
|------------------|--------|-------------|------------|-------------|----------------|------------------------------|
| Sample Number | | Client Info | | ML0001820 | ML0000582 | VCP314568 |
| Sample Date | | Client Info | | 23 May 2024 | 21 Mar 2024 | 16 Mar 2021 |
| Machine Age | hrs | Client Info | | 8637 | 8225 | 4070 |
| Oil Age | hrs | Client Info | | 412 | 4155 | 0 |
| Oil Changed | | Client Info | | N/A | Changed | Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINATION | ٧ | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >900 | 73 | 71 | 71 |
| Chromium | ppm | ASTM D5185m | >20 | <1 | <1 | <1 |
| Nickel | ppm | ASTM D5185m | >10 | 0 | <1 | <1 |
| Titanium | ppm | ASTM D5185m | | <1 | <1 | 1 |
| Silver | ppm | ASTM D5185m | | <1 | 0 | <1 |
| Aluminum | ppm | ASTM D5185m | >30 | 8 | 3 | <1 |
| Lead | ppm | ASTM D5185m | >50 | <1 | <1 | <1 |
| Copper | ppm | ASTM D5185m | >150 | 1 | 3 | 2 |
| Tin | ppm | ASTM D5185m | >20 | <1 | <1 | <1 |
| Antimony | ppm | ASTM D5185m | >5 | | | 0 |
| Vanadium | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Cadmium | ppm | ASTM D5185m | | <1 | <1 | <1 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 293 | 308 | 128 |
| Barium | ppm | ASTM D5185m | | 0 | 2 | 0 |
| Molybdenum | ppm | ASTM D5185m | | <1 | 1 | 3 |
| Manganese | ppm | ASTM D5185m | | 1 | 3 | 2 |
| Magnesium | ppm | ASTM D5185m | | 1 | 6 | 24 |
| Calcium | ppm | ASTM D5185m | | 15 | 97 | 104 |
| Phosphorus | ppm | ASTM D5185m | | 2384 | 2352 | 1050 |
| Zinc | ppm | ASTM D5185m | | 14 | 37 | 64 |
| Sulfur | ppm | ASTM D5185m | | 29495 | 31110 | 16921 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >50 | 26 | 11 | 0 |
| Sodium | ppm | ASTM D5185m | | 3 | 0 | 1 |
| Potassium | ppm | ASTM D5185m | >20 | 3 | 2 | 0 |
| VISUAL | | method | limit/base | current | history1 | history2 |
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | LIGHT | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | ted RyEService | Alex Anderson Page 1 of 2 |



OIL ANALYSIS REPORT



| FLUID PROPER | TIES | method | limit/base | current | history1 | history2 |
|--|-----------------------------|--|----------------------------|-------------|-----------------------------|-------------------------------|
| Visc @ 40°C | cSt | ASTM D445 | | 52.0 | 50.3 | 85.0 |
| SAMPLE IMAGE | S | method | limit/base | current | history1 | history2 |
| Oslar | | | | | | |
| Color | | | | no image | no image | no image |
| Bottom | | | | no image | no image | no image |
| Bottom | | | | no image | nomage | no image |
| GRAPHS | | | | | | |
| Ferrous Alloys | | | | | | |
| 300 - contraction chromium 250 - | | | | | | |
| 200 | | | | | | |
| 150- | | | | | | |
| 100 | | | | | | |
| | | | | | | |
| Dec5/18 Mar16/21 | | Mar21/24 | May23/24 | | | |
| Non-ferrous Meta | | | - | | | |
| 9 - copper second lead | | | | | | |
| | | | | | | |
| <u>ة</u> 5 | | | | | | |
| 4 | _ | ~ | | | | |
| 2 | | And a Description of the local distance of the | | | | |
| Dec5/18 0 | (Construction) | Mar21/24 | May23/24 | | | |
| ے Viscosity @ 40°C | | Mari | May | | | |
| 90 Abnormal | | | | | | |
| 80- | \ | | | | | |
| 75 2 70 | | | | | | |
| 0, 70 0⊕ 365 60 Abnognal | | | | | | |
| 55 | | | | | | |
| 50 | | | | | | |
| Dec5/18 Mar16/21 | | Mar21/24 | May23/24 | | | |
| _ | | _ | 4 | | | |
| : WearCheck USA - 5 : ML0001820 | 01 Madison Receiv | | NC 27513 May 2024 | MCCLUN | G-LOGAN EQUIPMEI 1345 MO | NT CO - RICHMOI JNTAIN ROA |
| : 06194450 : 11056573 | Tested Diagno | : 30 | May 2024 May 2024 - Ang | ala Davalla | | EN ALLEN, V US 2306 |



 Unique Number
 : 11056573
 Diagnosed
 : 30 May 2024 - Angela Borella

 Certificate 12367
 Test Package
 : CONST
 Co

 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 KRATLIFFE@N

 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 KRATLIFFE@N

 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

ACCLUNG-LOGAN EQUIPMENT CO- RICHMOND 1345 MOUNTAIN ROAD GLEN ALLEN, VA a US 23060 Contact: KYLE RATLIFFE KRATLIFFE@MCCLUNG-LOGAN.COM T: CGM 106:2012) F: (804)266-1611

Submitted By: Service - Alex Anderson Page 2 of 2