

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Machine Id

MOLDER 31 (S/N 202115036025935)

Component Hydraulic System

DYNOFLO AW 46 (35 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM		method	limit/base	current	history1	history2
Sample Number		Client Info		WC0937988	WC0848544	
Sample Date		Client Info		21 May 2024	10 Nov 2023	
Machine Age	hrs	Client Info		51210	1055	
Oil Age	hrs	Client Info		0	1055	
Oil Changed		Client Info		N/A	Not Changd	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	1	method	limit/base	current		history2
Water	4	WC Method		NEG	history1 NEG	TIISTOLAS
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	<1	0	
Chromium	ppm	ASTM D5185m	>20	<1	0	
Nickel	ppm	ASTM D5185m	>20	<1	0	
Titanium	ppm	ASTM D5185m		<1	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>20	2	0	
Lead	ppm	ASTM D5185m	>20	<1	0	
Copper	ppm	ASTM D5185m	>20	2	1	
Tin	ppm	ASTM D5185m	>20	<1	0	
Vanadium	ppm	ASTM D5185m		<1	0	
Cadmium	ppm	ASTM D5185m		<1	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m		<1	0	
Molybdenum	ppm	ASTM D5185m		<1	0	
Manganese	ppm	ASTM D5185m		0	0	
Magnesium	ppm	ASTM D5185m		2	0	
Calcium	ppm	ASTM D5185m		41	37	
Phosphorus	ppm	ASTM D5185m		330	389	
Zinc	ppm	ASTM D5185m		562	529	
Sulfur	ppm	ASTM D5185m		1322	994	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	5	2	
Sodium	ppm	ASTM D5185m		0	1	
Potassium	ppm	ASTM D5185m	>20	2	0	
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	3103	4181	
Particles >6µm		ASTM D7647	>1300	250	736	
Particles >14µm		ASTM D7647	>160	8	37	
Particles >21µm		ASTM D7647		3	9	
Particles >38µm		ASTM D7647	>10	0	0	
Particles >71µm		ASTM D7647		0	0	
Oil Cleanliness		ISO 4406 (c)	>19/17/14	19/15/10	19/17/12	
FLUID DEGRADA	TION _	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.58	0.47	
:51:54) Rev: 1	ing itoning	7 10 FW D0040			tion: JODIE LAF	


Report Id: ACTHIC [WUSCAR] 06195389 (Generated: 05/31/2024 14:51:54) Rev: 1


Contact/Location: JODIE LAFONE - ACTHIC Page 1 of 2



OIL ANALYSIS REPORT







Nov10/23

Pi Si	hite Metal		method	limit/base	current	history1	history2
— Pi Si	- II - · · · · · · · · · · · · · · · · ·	scalar	*Visual	NONE	NONE	NONE	
Si	ellow Metal	scalar	*Visual	NONE	NONE	NONE	
	recipitate	scalar	*Visual	NONE	NONE	NONE	
D	ilt	scalar	*Visual	NONE	NONE	NONE	
	ebris	scalar	*Visual	NONE	NONE	LIGHT	
Sa	and/Dirt	scalar	*Visual	NONE	NONE	NONE	
A	opearance	scalar	*Visual	NORML	NORML	NORML	
	dor	scalar	*Visual	NORML	NORML	NORML	
	mulsified Water	scalar	*Visual	>0.05	NEG	NEG	
Fr	ree Water	scalar	*Visual		NEG	NEG	
	FLUID PROPERT	ES	method	limit/base	current	history1	history2
Vi	sc @ 40°C	cSt	ASTM D445		46.6	46.5	
	SAMPLE IMAGES		method	limit/base	current	history1	history2
C	olor				a.	*	no image
						9	
					1000		
В	ottom						no image
	GRAPHS						
	Ferrous Alloys				Particle Count	:	
10 8	iron 1			491,520			1 ²
, i	nessessessessessessessessessessessessess			122,880 -			-2
udd 4				30,720	Severe		+2
2 -					1.1		
0	m				Abnormal		-2
	\sim			11/2			
	v10/			1,920-			-1
	Nov10/23			May21/24 cles (per 1 ml	1	•	-1
	Non-ferrous Metals			May 2,520 - 1,920 - 1,	1.		+1 +1
	Non-ferrous Metals			7,920 W avignment A 480 120	1.		+2 +1 -1 +1
10 8	Non-ferrous Metals			-084 battice			
¹⁰ T	Non-ferrous Metals						-1
10 8	Non-ferrous Metals						+1
	Non-ferrous Metals			30 - 8 -			-1
	Non-ferrous Metals			30 - 8 - 4 - 2 - 2 -			
	Non-ferrous Metals			30-		14μ 21μ	-1
	Viscosity @ 40°C			30- Balance Ba	Acid Number	14μ 21μ	+1
	Non-ferrous Metals			30- Balance Ba	Acid Number	14μ 21μ	+1
	Viscosity @ 40°C			30- Balance Ba	4 6j4 Acid Number	14μ 21μ	+1
10	Non-ferrous Metals			30- Balance Ba	Acid Number	14μ 21μ	+1
10 - 8	Viscosity @ 40°C			30- 8- 72/12/24 W (0,600 0,48- 0,40 0,48- 4, 0,0,0,0,0,0,0,0,0,0,0,0,0,0,0,0,0,0,	Acid Number	14μ 21μ	+1
10 4 4 2 0 55 50 50 50 50 50 50 50 50	Non-ferrous Metals			30 - 8 - 4 - 2 - 2 -	Acid Number	14μ 21μ	+1

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: ACTHIC [WUSCAR] 06195389 (Generated: 05/31/2024 14:51:54) Rev: 1

Certificate L2367

Contact/Location: JODIE LAFONE - ACTHIC

F:

T: (704)878-9991