

OIL ANALYSIS REPORT

Area ECORE LANCASTER Machine Id CM COOLING SCREW - ECORE LANCASTER

Gearbox Fluid

MOBIL OMALA S4 GXV 220 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend




NORMAL

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0892728		
Sample Date		Client Info		24 May 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	27		
Chromium	ppm	ASTM D5185m	>15	0		
Nickel	ppm	ASTM D5185m	>15	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>100	0		
Copper	ppm	ASTM D5185m	>200	0		
Tin	ppm	ASTM D5185m	>25	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		3		
Barium	ppm	ASTM D5185m		<1		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		3		
Phosphorus	ppm	ASTM D5185m		332		
Zinc	ppm	ASTM D5185m		16		
Sulfur	ppm	ASTM D5185m		10971		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	3		
Sodium	ppm	ASTM D5185m		1		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.47		



OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
May24,/24	Appearance	scalar	*Visual	NORML	NORML		
May	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPER	TIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		207		
	SAMPLE IMAGE	ES	method	limit/base	current	history1	history2
May24/24 +	Color					no image	no image
	Bottom					no image	no image
	Non-ferrous Meta	als		May24/24			
	E 6 4 2 0			lay24,24			
	Viscosity @ 40°C	:		May24/24	Acid Number		
	Viscosity @ 40°C	:		(BHQ) 0.40 (BHQ) 0.40 (BHQ) 0.30 (BHQ) 0.30 (BHQ) 0.30 (BHQ) 0.30 (BHQ) 0.30 (BHQ) 0.30 (BHQ) 0.30 (BHQ) 0.40 (BHQ) 0.40	Acid Number		
Laboratory Sample No. Lab Number	Viscosity @ 40°C		ived : 30	Mar24/24/24 Mar24/24/24 Action Mumber (mg K0H/g) 0.00 4 0.00	Acid Number	MOTOR TECH 515 WILLOW	

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: MOTYOR [WUSCAR] 06195593 (Generated: 05/31/2024 15:37:44) Rev: 1

Contact/Location: Bill Trimmer - MOTYOR

F: