

OIL ANALYSIS REPORT





IRGM01BE (S/N CTL0580)

Biogas Engine Fluid

CHEVRON HDAX 9500 GAS ENGINE OIL 40 (108 GAL)

DIAGNOSIS

Recommendation

We recommend that you drain the oil and perform a filter service on this component if not already done. We recommend an early resample to monitor this condition.

🔺 Wear

The tin level is abnormal. All other component wear rates are normal.

Contamination

Elemental level of silicon (Si) above normal.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0789116	WC0789115	WC0789114
Sample Date		Client Info		28 May 2024	22 May 2024	13 May 2024
Machine Age	hrs	Client Info		16713	16588	16468
Oil Age	hrs	Client Info		125	120	107
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				SEVERE	ABNORMAL	NORMAL
CONTAMINATION	J	method	limit/base	current	history1	history2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>.11	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	maa	ASTM D5185m	>15	10	12	4
Chromium	maa	ASTM D5185m	>4	<1	<1	0
Nickel	maa	ASTM D5185m		0	<1	0
Titanium	maa	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	maa	ASTM D5185m	>6	3	4	2
Lead	maa	ASTM D5185m	>9	6	3	1
Copper	mag	ASTM D5185m	>6	3	2	1
Tin	maa	ASTM D5185m	>4	5	▲ 5	<1
Vanadium	maa	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		22	23	8
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		11	16	9
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		48	44	34
Calcium	ppm	ASTM D5185m		1883	1834	2030
Phosphorus	maa	ASTM D5185m		373	322	368
Zinc	ppm	ASTM D5185m		452	433	463
Sulfur	ppm	ASTM D5185m		3458	3259	3352
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>181	2 16	174	109
Sodium	ppm	ASTM D5185m	>21	<1	1	1
Potassium	ppm	ASTM D5185m	>20	0	<1	<1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0.1	0.1	0
Nitration	Abs/cm	*ASTM D7624		6.0	5.8	5.4
Sulfation	Abs/.1mm	*ASTM D7415		21.3	19.8	18.0
FLUID DEGRADA		method	limit/base	current	history1	history2
Oxidation	Abs/,1mm	*ASTM D7414		13.2	11.9	10.0
Acid Number (AN)	ma KOH/a	ASTM D8045	10	2.29	1 32	0.64
			1.0	2.20	1.06	0.04
Base Number (BN)	ma KOH/a	ASTM D0040	5.4	3.72	3.38	4.54



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
Vhite Metal	scalar	*Visual	NONE	NONE	NONE	NONE
ellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
recipitate	scalar	*Visual	NONE	NONE	NONE	NONE
lilt	scalar	*Visual	NONE	NONE	NONE	NONE
ebris	scalar	*Visual	NONE	NONE	NONE	NONE
and/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
ppearance	scalar	*Visual	NORML	NORML	NORML	NORML
dor	scalar	*Visual	NORML	NORML	NORML	NORML
mulsified Water	scalar	*Visual	>.11	NEG	NEG	NEG
ree Water	scalar	*Visual		NEG	NEG	NEG
		mathad	limit/booo	ourropt	biotorut	biotory ()
	IEO	method	iimii/base	current	nistory i	nistoryz
′isc @ 100°C	cSt	ASTM D445	13.4	13.7	13.7	13.4









Received

Diagnosed

Tested



Chromium (ppm)





Base Number

-h71/73

Dec2/19

8

6 Der

21 ase

0.0

: 30 May 2024

: 31 May 2024

lec4/18

(B/HOX Bu)



pr17/23

un1/23 Vov29/23

Report Id: ENEJOH [WUSCAR] 06195612 (Generated: 06/03/2024 21:30:04) Rev: 1

Submitted By: CHRIS SMITH

May3/24