OIL ANALYSIS REPORT

Sample Rating Trend



DIRT

Area
DICK LAVY
Machine Id
DICK LAVY 4819
Component
Rear Differential
Fluid
GEAR OIL SAE 75W90 (--- GAL)

DIAGNOSIS

Recommendation
We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is a high amount of particulates present in the oil. Elemental level of silicon (Si) above normal indicating ingress of seal material.

Fluid Condition
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**WC0934562**	WC0900748	WC0900895
Sample Date		Client Info		**07 May 2024**	11 Apr 2024	04 Jan 2024
Machine Age	mls	Client Info		**493921**	493798	457388
Oil Age	mls	Client Info		**0**	0	0
Oil Changed		Client Info		**N/A**	N/A	N/A
Sample Status				**ABNORMAL**	ABNORMAL	ABNORMAL

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	**147**	144	149
Chromium	ppm	ASTM D5185m	>10	**<1**	<1	<1
Nickel	ppm	ASTM D5185m	>10	**0**	<1	0
Titanium	ppm	ASTM D5185m		**<1**	<1	0
Silver	ppm	ASTM D5185m		**0**	0	0
Aluminum	ppm	ASTM D5185m	>25	**3**	2	1
Lead	ppm	ASTM D5185m	>25	**0**	0	0
Copper	ppm	ASTM D5185m	>100	**1**	2	1
Tin	ppm	ASTM D5185m	>10	**<1**	2	<1
Vanadium	ppm	ASTM D5185m		**<1**	0	0
Cadmium	ppm	ASTM D5185m		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	**267**	287	241
Barium	ppm	ASTM D5185m	200	**1**	2	<1
Molybdenum	ppm	ASTM D5185m	12	**0**	0	0
Manganese	ppm	ASTM D5185m		**10**	11	11
Magnesium	ppm	ASTM D5185m	12	**4**	4	1
Calcium	ppm	ASTM D5185m	150	**8**	9	8
Phosphorus	ppm	ASTM D5185m	1650	**1354**	1411	1337
Zinc	ppm	ASTM D5185m	125	**15**	9	<1
Sulfur	ppm	ASTM D5185m	22500	**25218**	26453	21152

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	▲ **83**	▲ 86	▲ 89
Sodium	ppm	ASTM D5185m		**6**	5	5
Potassium	ppm	ASTM D5185m	>20	**1**	3	<1
Water	%	ASTM D6304	>.2	**0.039**	0.032	0.017
ppm Water	ppm	ASTM D6304	>2000	**392**	328	173

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	▲ **202206**	▲ 53250	▲ 62514
Particles >6µm		ASTM D7647	>5000	▲ **69868**	1774	2503
Particles >14µm		ASTM D7647	>640	▲ **3789**	19	32
Particles >21µm		ASTM D7647	>160	▲ **565**	6	5
Particles >38µm		ASTM D7647	>40	**7**	0	1
Particles >71µm		ASTM D7647	>10	**0**	0	0
Oil Cleanliness		ISO 4406 (c)	>21/19/16	▲ **25/23/19**	▲ 23/18/11	▲ 23/19/12

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	2.00	**2.71**	2.18	2.17

OIL ANALYSIS REPORT

Particle Trend



Silicon (ppm)



Water (KF)



Viscosity @ 100°C



Water (KF)



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	109	**113**	112	114
Visc @ 100°C	cSt	ASTM D445	16.0	**15.2**	15.3	15.4
Viscosity Index (VI)	Scale	ASTM D2270	157	**140**	143	141

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					



GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Particle Count



Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0934562 **Received** : 30 May 2024
Lab Number : 06195914 **Tested** : 02 Jun 2024
Unique Number : 11058037 **Diagnosed** : 02 Jun 2024 - Doug Bogart
Test Package : MOB 2 (Additional Tests: KF, KV100, PrtCount, VI)

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

BASF - GIANNA CREDAROLI
500 WHITE PLAINS RD
TARRYTOWN, NY
US 10591
Contact: MIKE BARRY
mike.barry@basf.com
T:
F: