

OIL ANALYSIS REPORT

Sample Rating Trend





[146479] LINK-BELT TCC-800 U1L2-7108 Component Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

SAMPLE INFORMATION method LBC0000107 Sample Number **Client Info** Sample Date Client Info 28 May 2024 Client Info Machine Age hrs 297 Oil Age hrs Client Info 0 Oil Changed Not Changd **Client Info** Sample Status NORMAL CONTAMINATION Fuel >5 WC Method <1.0 Water WC Method >0.2 NEG Glycol WC Method NEG WEAR METALS >100 15 Iron ppm ASTM D5185m Chromium ASTM D5185m >20 0 ppm Nickel n ppm ASTM D5185m >4 Titanium ppm ASTM D5185m <1 Silver ASTM D5185m >3 0 ppm 2 Aluminum ASTM D5185m >20 ppm >40 0 Lead ASTM D5185m ppm ASTM D5185m >330 32 Copper ppm Tin ppm ASTM D5185m >15 <1 Vanadium ppm ASTM D5185m 0 Cadmium 0 ASTM D5185m ppm Boron mag ASTM D5185m 250 84 Barium ASTM D5185m 10 10 ppm 10 Molybdenum ASTM D5185m 100 ppm ASTM D5185m Manganese ppm 4 Magnesium ASTM D5185m 450 746 ppm Calcium ppm ASTM D5185m 3000 1271 Phosphorus ASTM D5185m 1150 1032 ppm Zinc ppm ASTM D5185m 1350 1143 Sulfur ASTM D5185m 4250 3981 ppm Silicon ASTM D5185m >25 34 ppm Sodium ASTM D5185m >158 ppm 5 Potassium ASTM D5185m >20 4 ppm **INFRA-RED** % 0.1 Soot % *ASTM D7844 >3 Nitration Abs/cm *ASTM D7624 >20 8.3 Sulfation *ASTM D7415 >30 19.9 Abs/.1mm FLUID DEGRADATION *ASTM D7414 >25 14.8 Oxidation Abs/.1mm Base Number (BN) mg KOH/g ASTM D2896 8.5 8.0

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

Metal levels are typical for a new component breaking in.

Contamination


There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.



OIL ANALYSIS REPORT



Contact/Location: JASON LANG - LBCP103900