

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area CS-46 [PM6-3141408] KAESER 1379 - DESIGN WORKSHOP

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		UCH06196780			
Sample Date		Client Info		06 May 2024			
Machine Age	hrs	Client Info		38964			
Oil Age	hrs	Client Info		678			
Oil Changed		Client Info		Changed			
Sample Status				NORMAL			
CONTAMINATION		method	limit/base	current	history1	history2	
Water		WC Method	>0.05	NEG			
WEAR METALS		method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>50	0			
Chromium	ppm	ASTM D5185m	>10	۔ <1			
Nickel	ppm	ASTM D5185m	>3	0			
Titanium	ppm	ASTM D5185m	>3	<1			
Silver	ppm	ASTM D5185m	>2	0			
Aluminum	ppm	ASTM D5185m		2			
Lead	ppm	ASTM D5185m	>10	- <1			
Copper	ppm	ASTM D5185m	>50	2			
Tin	ppm	ASTM D5185m	>10	- <1			
Vanadium	ppm	ASTM D5185m		0			
Cadmium	ppm	ASTM D5185m		0			
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	1.5	0			
Barium	ppm	ASTM D5185m	0	<1			
Molybdenum	ppm	ASTM D5185m	0	<1			
Manganese	ppm	ASTM D5185m	0.3	0			
Magnesium	ppm	ASTM D5185m	0	2			
Calcium	ppm	ASTM D5185m	0	0			
Phosphorus	ppm	ASTM D5185m	406	186			
Zinc	ppm	ASTM D5185m	0	20			
Sulfur	ppm	ASTM D5185m	1283	6671			
CONTAMINANTS		method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>25	5			
Sodium	ppm	ASTM D5185m		0			
Potassium	ppm	ASTM D5185m	>20	1			
FLUID DEGRADA		method	limit/base	current	history1	history2	
Acid Number (AN)	mg KOH/g	ASTM D8045	0.463	0.21			



OIL ANALYSIS REPORT





	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
/24 -	Appearance	scalar	*Visual	NORML	NORML		
May6/24	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.05	NEG		
	Free Water	scalar	*Visual	>0.05	NEG		
					NEG		
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	47.9	45.3		
	SAMPLE IMAGES	\$	method	limit/base	current	history1	history2
May6/24	Color					no image	no image
	Bottom					no image	no image
	Non-ferrous Metals	5		May6/24			
	Viscosity @ 40°C				Acid Number		
	(2-0-0-1) 23 45 45 45 45 45 45 45 45 45 45			May6/24 Acid Number (mg KOH(g) 0.0 Acid Number (mg KOH(g) 0.0 Acid Number (mg KOH(g) 0.0 Acid Number (mg KOH(g) 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	May6/24		
Laboratory Sample No. Lab Number Unique Number Test Package discuss this sample report,	: UCH06196780 : 06196780 : 11058903 : IND 2	Recei Teste Diagr	ladison Ave., Cary, NC 27513 Received : 31 May 2024 Tested : 03 Jun 2024 Diagnosed : 03 Jun 2024 - Wes Davis at 1-800-237-1369. 25 scope of accreditation.			CISCO AIR SYSTEM 214 27TH S SACRAMENTO, C US 958 Contact: BARRY FRKOVIC barryfrkovich@ciscoair.co T: (916)444-252	

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: UCCISSAC [WUSCAR] 06196780 (Generated: 06/04/2024 07:26:48) Rev: 1

Contact/Location: BARRY FRKOVICH - UCCISSAC

F: x: