

## **OIL ANALYSIS REPORT**

Area PG-46 [277331] PNEUTECH AK100008444 - NODEC MOTOR Component

Component Compressor

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

## Wear


All component wear rates are normal.

## Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend




NORMAL

SAMPLE INFORM	<b>MATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		UFD0000883		
Sample Date		Client Info		14 Feb 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	0		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		15		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		<1		
Phosphorus	ppm	ASTM D5185m		92		
Zinc	ppm	ASTM D5185m		3		
Sulfur	ppm	ASTM D5185m		0		
CONTAMINANTS	5	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0		
Sodium	ppm	ASTM D5185m		4		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.083		



# **OIL ANALYSIS REPORT**

VISUAI



	VISUAL		method	limit/base	currer	nt history1	history2	
	White Metal	scalar	*Visual	NONE	NONE			
	Yellow Metal	scalar	*Visual	NONE	NONE			
	Precipitate	scalar	*Visual	NONE	NONE			
	Silt	scalar	*Visual	NONE	NONE			
	Debris	scalar	*Visual	NONE	NONE			
	Sand/Dirt	scalar	*Visual	NONE	NONE			
Feb 14/24	Appearance	scalar	*Visual	NORML	NORML			
- P	Odor	scalar	*Visual	NORML	NORML			
	Emulsified Water	scalar	*Visual	>0.1	NEG			
	Free Water	scalar	*Visual		NEG			
	FLUID PROPERT	IES	method	limit/base	currer	nt history1	history2	
						· · · · · · · · · · · · · · · · · · ·	motoryz	
1	Visc @ 40°C	cSt	ASTM D445		42.9			
	SAMPLE IMAGES	6	method	limit/base	currer	nt history1	history2	
Feb14/24	Color					no image	no image	
	Bottom					no image	no image	
	Non-ferrous Metals	5		Feb14/24 Feb14/24 Feb14/24 Feb14/24	Acid Num	nber		
	(2-0+) 45 40 35 40 40 40 40			24 .0 Acid Number (ma .0	10		20	
	Feb14/24			Feb14/24	Feb14/24		Feb 14/24	
unique Number rificate L2367 Test Package discuss this sample report, Denotes test methods that	b. : UFD0000883 Received : 03 Jun 2024   per : 06197800 Tested : 05 Jun 2024   ber : 11059923 Diagnosed : 05 Jun 2024 - Wes David					Contact: ED DIENEF ed.diener@fluidairedynamics.com T: (847)678-8388		

Contact/Location: ED DIENER - UCFLUSCH