


OIL ANALYSIS REPORT

SFG 200 [284263] **GARDNER DENVER S087690 - SCHOLLE**

Component Compressor





Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Moderate concentration of visible dirt/debris present in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UFD0001208	UFD0000328	
Sample Date		Client Info		02 May 2024	11 Oct 2023	
Machine Age	hrs	Client Info		24474	0	
Oil Age	hrs	Client Info		0	0	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	ATTENTION	
CONTAMINATION	V	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	
Chromium	ppm	ASTM D5185m	>10	0	0	
Nickel	ppm	ASTM D5185m		0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	0	0	
Lead	ppm	ASTM D5185m	>25	0	0	
Copper	ppm	ASTM D5185m	>50	6	8	
Tin	ppm	ASTM D5185m	>15	0	0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	<1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m		0	0	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		0	<1	
Magnesium	ppm	ASTM D5185m		0	2	
Calcium	ppm	ASTM D5185m		0	5	
Phosphorus	ppm	ASTM D5185m		270	351	
Zinc	ppm	ASTM D5185m		0	5	
Sulfur	ppm	ASTM D5185m		0	155	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1	<1	
Sodium	ppm	ASTM D5185m		1	3	
Potassium	ppm	ASTM D5185m	>20	3	25	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		1.34	0.29	




OIL ANALYSIS REPORT





VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	MODER	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.1	NEG	0.2%	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		49.0	51.0	
SAMPLE IMAGES		method	limit/base	current	history1	history2




GRAPHS













Certificate 12367

Laboratory

Test Package : IND 2

Sample No. : UFD0001208 Lab Number : 06197809

Unique Number : 11059932

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 03 Jun 2024 Tested : 04 Jun 2024

Diagnosed : 04 Jun 2024 - Don Baldridge

225 SPRING LAKE DR ITASCA, IL US 60143

FLUID-AIRE DYNAMICS

Contact: ED DIENER ed.diener@fluidairedynamics.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: UCFLUSCH [WUSCAR] 06197809 (Generated: 06/04/2024 15:19:32) Rev: 1

Contact/Location: ED DIENER - UCFLUSCH

T: (847)678-8388