




OIL ANALYSIS REPORT



Area
OKLAHOMA/1052
 Machine Id
45.58L [OKLAHOMA^1052]
 Component
Diesel Engine
 Fluid
MOBIL DELVAC 1300 SUPER15W40 (5 GAL)

Sample Rating Trend



NORMAL



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0935128	WC0848875	WC0857433
Sample Date	Client Info		28 May 2024	09 Apr 2024	13 Feb 2024
Machine Age	hrs	Client Info	8282	7983	7499
Oil Age	hrs	Client Info	250	263	250
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method		<1.0	<1.0	<1.0
Water	WC Method		NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	5	8	6
Chromium	ppm	ASTM D5185m	0	0	0
Nickel	ppm	ASTM D5185m	0	0	<1
Titanium	ppm	ASTM D5185m	0	0	0
Silver	ppm	ASTM D5185m	0	0	0
Aluminum	ppm	ASTM D5185m	2	3	3
Lead	ppm	ASTM D5185m	0	0	0
Copper	ppm	ASTM D5185m	0	0	0
Tin	ppm	ASTM D5185m	0	0	0
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	49	41	55
Barium	ppm	ASTM D5185m	0	0	0
Molybdenum	ppm	ASTM D5185m	39	41	40
Manganese	ppm	ASTM D5185m	<1	0	0
Magnesium	ppm	ASTM D5185m	509	540	555
Calcium	ppm	ASTM D5185m	1760	1839	1834
Phosphorus	ppm	ASTM D5185m	760	812	828
Zinc	ppm	ASTM D5185m	938	969	995
Sulfur	ppm	ASTM D5185m	2955	3221	2827

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	3	3	4
Sodium	ppm	ASTM D5185m	1	2	2
Potassium	ppm	ASTM D5185m	<1	0	0

INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	0.2	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	7.6	6.9	6.2
Sulfation	Abs/.1mm	*ASTM D7415	22.0	21.5	21.4

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	21.0	20.4	19.8
Base Number (BN)	mg KOH/g	ASTM D2896	9.3	9.3	9.5







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	NEG	NEG	NEG
Free Water	scalar	*Visual	NEG	NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.6	12.6	12.6

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0935128 **Received** : 05 Jun 2024
Lab Number : 06199957 **Tested** : 06 Jun 2024
Unique Number : 11062080 **Diagnosed** : 06 Jun 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

SHERWOOD CONSTRUCTION CO INC
 3219 WEST MAY ST
 WICHITA, KS
 US 67213
 Contact: SHAWN SOUTH
 shawn.south@sherwood.net

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)