


OIL ANALYSIS REPORT

Sample Rating Trend







DWP-2C
Component
Gear Drive

ROYAL PURPLE SYNFILM GT 32 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear

All component wear rates are normal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


laci019 Jani020 Apri021 Octi021 Octi022 Juli023 Mari024						
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		RP0043297	RP0039427	RP0038809
Sample Date		Client Info		04 Jun 2024	31 Mar 2024	10 Dec 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>150	6	0	<1
Chromium	ppm	ASTM D5185m	>10	0	<1	0
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	0	0	<1
Lead	ppm	ASTM D5185m	>100	0	0	0
Copper	ppm	ASTM D5185m	>50	<1	<1	<1
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		83	78	88
Calcium	ppm	ASTM D5185m		4	3	2
Phosphorus	ppm	ASTM D5185m		15	8	5
Zinc	ppm	ASTM D5185m		4	3	0
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	1	1	1
Sodium	ppm	ASTM D5185m		1	2	<1
Potassium	ppm	ASTM D5185m	>20	0	0	1
Water	%	ASTM D6304	>0.1	0.021	0.011	0.016
ppm Water	ppm	ASTM D6304	>1000	212	117	167
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.39	0.42	0.43
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG


TERTISE SAUVEUR NEW GBOS



OIL ANALYSIS REPORT












GRAPHS Ferrous Alloys 30 15 10











Certificate 12367

Laboratory Sample No.

: RP0043297 Lab Number : 06200268 Unique Number : 11062391 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 05 Jun 2024 **Tested** : 06 Jun 2024

Diagnosed : 06 Jun 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

robert.stsauveur@engie.com T: (401)651-9381 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: ENGBOS [WUSCAR] 06200268 (Generated: 06/06/2024 15:08:07) Rev: 1

Contact/Location: ROBERT ST SAUVEUR - ENGBOS

ENGIE-MATEP

BOSTON, MA

US 02215

474 BROOKLINE AVE

Contact: ROBERT ST SAUVEUR