

# **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL

Machine Id LEO CUTTER Component Hydraulic System Fluid {not provided} (--- GAL)

#### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

## Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


### Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		HRE0000619		
Sample Date		Client Info		05 Jun 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIC	N	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	10		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	4		
Lead	ppm	ASTM D5185m	>20	0		
Copper	ppm	ASTM D5185m	>20	2		
Tin	ppm	ASTM D5185m	>20	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		1		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		4		
Calcium	ppm	ASTM D5185m		95		
Phosphorus	ppm	ASTM D5185m		506		
Zinc	ppm	ASTM D5185m		646		
Sulfur	ppm	ASTM D5185m		1536		
CONTAMINANT	S	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	2		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	2		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.05	NEG		
Free Water	scalar	*Visual		NEG		
:54:18) Rev: 1	Contact/Location: KENNY JR ? - HMLSO					



# **OIL ANALYSIS REPORT**



FLUID PROPE		method	limit/base	current	history1	history2
/isc @ 40°C	cSt	ASTM D445		58.9		
SAMPLE IMAG	iES	method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image
GRAPHS						
Ferrous Alloys						
iron						
nickel						
-						
Jun5/24			Jun5/24			
Non-ferrous Me	tale		,			
Non-remous Me	lais					
copper						
tin						
-						
•						
724			/24			
Jun5/24			Jun5/24			
Viscosity @ 40°	С					
T						
Abnormal						
Abnormal						
/24			/24			
Jun5/24			Jun5/24			
earCheck USA -	501 Madis	on Ave Carv	NC 27513		на	& M LOGGIN
RE0000619	Rece	eived : 05	Jun 2024			1180 SINAI R
6200981	Test	ed : 06	Jun 2024			BOSTON, V



Contact/Location: KENNY JR ? - HMLSOU Page 2 of 2