

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

KOHLER BLACKSBURG UFD

Component

Diesel Engine

NAPA Motor Oil 15W40 (--- GAL)

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

				May2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0901710		
Sample Date		Client Info		30 May 2024		
Machine Age	hrs	Client Info		1234		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATIO	V	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method		NEG		
Glycol		WC Method	7 0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	2		
Chromium	ppm	ASTM D5185m	>20	- <1		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	3		
Lead	ppm	ASTM D5185m	>40	<1		
Copper	ppm	ASTM D5185m	>330	<1		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		32		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		17		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		40		
Calcium	ppm	ASTM D5185m		2286		
Phosphorus	ppm	ASTM D5185m		1019		
Zinc	ppm	ASTM D5185m		1097		
Sulfur	ppm	ASTM D5185m		4044		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	2		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0		
Nitration	Abs/cm	*ASTM D7624	>20	5.9		
Sulfation	Abs/.1mm	*ASTM D7415	>30	15.5		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	9.7		
Base Number (BN)	mg KOH/g	ASTM D2896		7.5		



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
		and the section of	11.00 21.00 0000		late to mod	la la La ma O


FLUID PROPER	HES	metnoa	ilmit/base	current	nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445		13.4		


GRAPHS



- 1	copper		
	eeeeeeeeeeeeeeee lead		
8+	**************************************		
6 -			
4			
2 -			

	May30).24		May30/24









Certificate 12367

Laboratory Sample No.

: WC0901710 Lab Number : 06202277 Unique Number : 11069738

Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 06 Jun 2024 Tested : 11 Jun 2024 Diagnosed

: 11 Jun 2024 - Jonathan Hester

CAROLINA POWER SOLUTION 445 W GROVER ST SHELBY, NC US 28150

Contact: PAIGE paige@carolinapowersolutions.com

T: (704)481-0782

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)