

OIL ANALYSIS REPORT

Sample Rating Trend

ISO

Machine Id DC-1 (S/N E1505) Refrigeration Compressor Fluid USPI 1009-68 SC (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 6 microns in size) present in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP0012492	USP0004451	USP255277
Sample Date		Client Info		06 Jun 2024	17 Dec 2023	23 Aug 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ATTENTION	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	2	9	15
Chromium	ppm	ASTM D5185m	>2	<1	0	0
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	0	0	0
Lead	ppm	ASTM D5185m	>2	0	0	0
Copper	ppm	ASTM D5185m	>8	0	0	0
Tin	ppm	ASTM D5185m	>4	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		<1	0	0
Calcium	ppm	ASTM D5185m		0	0	0
Phosphorus	ppm	ASTM D5185m		<1	0	<1
Zinc	ppm	ASTM D5185m		3	0	0
Sulfur	ppm	ASTM D5185m	50	0	0	4
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	0	<1	0
Sodium	ppm	ASTM D5185m		0	<1	0
Potassium	ppm	ASTM D5185m	>20	<1	0	0
Water	%	ASTM D6304	>0.01	0.004	0.003	0.004
ppm Water	ppm	ASTM D6304	>100	48	29	40.5
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	e 11221	665	1234
Particles >6µm						
Particles >14µm		ASTM D7647		2090	215	345
r anticles >14µm		ASTM D7647 ASTM D7647	>2500 >320	2090 21	215 14	345 42
Particles >21µm			>320			
•		ASTM D7647	>320	21	14	42
Particles >21µm Particles >38µm Particles >71µm		ASTM D7647 ASTM D7647	>320 >80 >20 >4	21 3	14 5	42 12 0 0
Particles >21µm Particles >38µm		ASTM D7647 ASTM D7647 ASTM D7647	>320 >80 >20	21 3 0	14 5 0	42 12 0
Particles >21µm Particles >38µm Particles >71µm	TION	ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>320 >80 >20 >4	21 3 0 0	14 5 0 0	42 12 0 0


Contact/Location: benjamin evans - CONIND Page 1 of 2





OIL ANALYSIS REPORT












VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	67	70.1	68.6	69.0
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
Color				•		

Bottom



To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: CONIND [WUSCAR] 06202800 (Generated: 06/11/2024 12:28:43) Rev: 1

Certificate 12367

Contact/Location: benjamin evans - CONIND

benjamin.evans@conagra.com

Page 2 of 2

F: x:

T: (317)554-6078