




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
PACKAGING CUB
 Machine Id
PVAC 2 (S/N 259171-1106)
 Component
Pump
 Fluid
KV100 (2 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WCI2340258	WCI2340254	WCI2340146
Sample Date	Client Info		30 May 2024	03 Apr 2024	19 Feb 2024
Machine Age	hrs	Client Info	54846	54159	53640
Oil Age	hrs	Client Info	690	500	500
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>.1	NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >90	0	0	<1
Chromium	ppm	ASTM D5185m >5	0	0	0
Nickel	ppm	ASTM D5185m >5	0	<1	<1
Titanium	ppm	ASTM D5185m >3	0	0	<1
Silver	ppm	ASTM D5185m >3	0	0	<1
Aluminum	ppm	ASTM D5185m >7	0	<1	<1
Lead	ppm	ASTM D5185m >12	0	<1	<1
Copper	ppm	ASTM D5185m >30	0	0	1
Tin	ppm	ASTM D5185m >9	0	<1	<1
Vanadium	ppm	ASTM D5185m	<1	0	0
Cadmium	ppm	ASTM D5185m	0	0	<1

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0
Barium	ppm	ASTM D5185m	2	0	5
Molybdenum	ppm	ASTM D5185m	0	0	1
Manganese	ppm	ASTM D5185m	0	<1	<1
Magnesium	ppm	ASTM D5185m	<1	2	7
Calcium	ppm	ASTM D5185m	9	12	16
Phosphorus	ppm	ASTM D5185m	4	7	0
Zinc	ppm	ASTM D5185m	8	<1	13
Sulfur	ppm	ASTM D5185m	7957	9096	8605

CONTAMINANTS


	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >60	6	6	10
Sodium	ppm	ASTM D5185m	4	3	0
Potassium	ppm	ASTM D5185m >20	0	2	<1

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.074	0.088	0.246




OIL ANALYSIS REPORT







VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	114	112	114

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC12340258 **Received** : 07 Jun 2024
Lab Number : **06202937** **Tested** : 10 Jun 2024
Unique Number : 11070398 **Diagnosed** : 10 Jun 2024 - Don Baldrige
Test Package : IND 2

QORVO
 7914 PIEDMONT TRIAD PKWY
 GREENSBORO, NC
 US 27409
 Contact: JIM AGNER
 jim.agner@qorvo.com
 T: (336)678-5038
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)