


OIL ANALYSIS REPORT

Sample Rating Trend







CATERPILLAR D6 10030 (S/N JJ601009)

Right Final Drive

{not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil

Fluid Condition

The condition of the oil is acceptable for the time in service.


.)		Aug2022 D	lec2022 Jun2023 Aug20	23 Oct2023 Nov2023 Feb2024	Jun2024	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0899259	WC0888052	WC0879398
Sample Date		Client Info		04 Jun 2024	06 Feb 2024	20 Nov 2023
Machine Age	hrs	Client Info		3880	3483	2920
Oil Age	hrs	Client Info		399	556	244
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>800	5	3	4
Chromium	ppm	ASTM D5185m	>10	<1	<1	0
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m	>15	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>75	0	0	0
ead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>75	0	0	<1
- in	ppm	ASTM D5185m	>8	0	0	0
/anadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		178	168	168
Barium	ppm	ASTM D5185m		0	<1	0
Nolybdenum	ppm	ASTM D5185m		4	0	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
/lagnesium	ppm	ASTM D5185m		31	0	0
Calcium	ppm	ASTM D5185m		605	51	87
Phosphorus	ppm	ASTM D5185m		467	334	322
Zinc	ppm	ASTM D5185m		215	11	24
Sulfur	ppm	ASTM D5185m		2620	1749	1721
CONTAMINANTS	5	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	3	1	3
Sodium	ppm	ASTM D5185m		<1	0	2
Potassium	ppm	ASTM D5185m	>20	<1	0	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
ellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
ree Water	scalar	*Visual		NEG	NEG	NEG
55:09) Rev: 1					ation: MIKE WY	





OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		95.3	97.3	99.9
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image











Certificate 12367

Laboratory

Sample No. : WC0899259 Lab Number : 06203106 Unique Number : 11070567 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 07 Jun 2024 Tested : 10 Jun 2024

: 10 Jun 2024 - Wes Davis Diagnosed

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Contact: MIKE WYATT mwyatt@traderconstruction.com T: (252)633-1399

TRADER CONSTRUCTION CO.

PO DRAWER 1578

NEW BERN, NC

US 28563

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (252)638-4871 Contact/Location: MIKE WYATT - TRANEW