

OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area **MINING** ME-022 CATERPILLAR 980 WFX00241 **Rear Right Final Drive**


MOBIL MOBILTRANS HD 50 (--- GAL)

DIAGNOSIS SAMPLE INFORMATION method WC0929523 Sample Number **Client Info** Recommendation Resample at the next service interval to monitor. 05 Jun 2024 Sample Date Client Info Machine Age hrs **Client Info** 6311 Wear All component wear rates are normal. Oil Age hrs Client Info 500 Oil Changed Client Info Not Changd Contamination Sample Status NORMAL There is no indication of any contamination in the oil CONTAMINATION Fluid Condition WC Method >0.2 NEG Water The condition of the oil is acceptable for the time in service. WEAR METALS ppm ASTM D5185m >800 103 Iron Chromium ASTM D5185m >10 <1 ppm Nickel 0 ppm ASTM D5185m >5 Titanium ASTM D5185m >15 <1 ppm Silver >2 0 ppm ASTM D5185m Aluminum ppm ASTM D5185m >75 2 Lead ASTM D5185m >10 0 ppm 43 Copper ppm ASTM D5185m >75 0 Tin ASTM D5185m >8 ppm Vanadium 0 ppm ASTM D5185m Cadmium 0 ppm ASTM D5185m 0 Boron ASTM D5185m ppm Barium ppm ASTM D5185m 0 Molvbdenum ASTM D5185m <1 ppm ASTM D5185m 2 Manganese ppm Magnesium ASTM D5185m 12 ppm Calcium ASTM D5185m 3028 ppm Phosphorus ASTM D5185m 1033 ppm Zinc ppm ASTM D5185m 1268 Sulfur ASTM D5185m 4976 ppm Silicon ppm ASTM D5185m >400 11 Sodium ASTM D5185m <1 ppm Potassium ASTM D5185m >20 0 ppm VISUAL White Metal scalar *Visual NONE NONE Yellow Metal *Visual NONE NONE scalar Precipitate *Visual NONE NONE scalar Silt scalar *Visual NONE NONE Debris *Visual NONE NONE scalar Sand/Dirt scalar *Visual NONE NONE *Visual Appearance NORML NORML scalar Odor NORML NORML scalar *Visual **Emulsified Water** NEG scalar *Visual >0.2 Free Water scalar *Visual NEG Submitted By: Chris Bowers


Report Id: COVLUG [WUSCAR] 06203115 (Generated: 06/10/2024 09:50:26) Rev: 1



OIL ANALYSIS REPORT



FLUID PROPER	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	195	193		
SAMPLE IMAGE	ES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						
Ferrous Alloys			Jun524			
Non-ferrous Meta	als					
40 sease lead 35 30 4						
25 - 20 -						
15- 10- 5-						
Jun5/24 0			Jun5/24			
Viscosity @ 40°C	;					
220						
200 - 9-202						
190						
160 - 150 -						
140 Abnormal						
Jun5/24			Jun5/24			
WearCheck USA - 5 WC0929523	01 Madisc Rece	n Ave., Cary ived : 07				LUGOFF - 023 CREEK ROAD



Submitted By: Chris Bowers Page 2 of 2