

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id **7 CO** Component **Gearbox** Fluid

{not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


Viscosity of sample indicates oil is within ISO 460 range, advise investigate. Confirm oil type. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC06203472		
Sample Date		Client Info		28 May 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	2		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>50	0		
Copper	ppm	ASTM D5185m	>200	0		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		5		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		1		
Calcium	ppm	ASTM D5185m		1		
Phosphorus	ppm	ASTM D5185m		177		
Zinc	ppm	ASTM D5185m		<1		
Sulfur	ppm	ASTM D5185m		7717		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	3		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.77		



OIL ANALYSIS REPORT

VISUAL



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
1	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
8/24 -	Appearance	scalar	*Visual	NORML	NORML		
May28/24	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
	Free Water	scalar	*Visual		NEG		
				line it //e e e e		lata ta mut	bister 0
	FLUID PROPERT		method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		460		
	SAMPLE IMAGES	;	method	limit/base	current	history1	history2
May28/24 +	Color				no image	no image	no image
	Bottom				no image	no image	no image
	GRAPHS Iron (ppm)			20 톱 10	Severe		
	Aluminum (ppm)				Chromium (p	pm)	
	Mind 50 - Abnormal			May28/24	Abnormal 0 + 72/82/82 0 + 72/82/82		
	Copper (ppm)			15	Silicon (ppm)		
	E 400 Severe			<u>الم</u>	0 Severe		
	B 200 - Abnormal			ă ș	0 - Abnormal		
	8/24 L			8/24	8/24		
	May28/24			May28/24	May28/2 ⁴		
	Viscosity @ 40°C			5/24 Acid Number (mg K0H/g)	Acid Number		
				E B			
	्रि. 400 - सु 200 -						
	0			24 - 0.0			
	ay 28/.			ay28/. A	ay28/,		
Laboratory Sample No. Lab Number Unique Number Test Package discuss this sample report	: 11070933 : MOB 2	Recei Teste Diagr	ived : 07 id : 12 nosed : 12	r, NC 27513 7 Jun 2024 2 Jun 2024 Jun 2024 - Anç	May2	F	R Incorporate P.O. Box 195 Atlanta, C US 303 JOHN STEE d@momar.cc

Report Id: MOMATL [WUSCAR] 06203472 (Generated: 06/12/2024 09:07:12) Rev: 1

Contact/Location: JOHN STEED - MOMATL