

OIL ANALYSIS F

Particles >38µm

Particles >71µm

Oil Cleanliness

Acid Number (AN)

FLUID DEGRADATION

ASTM D7647

ASTM D7647

ISO 4406 (c)

method

mg KOH/g ASTM D8045

>40

>10

>21/19/16

limit/base

0

0

23/21/15

0.76

current

Area **Paper Machine Reel Drum Drive Gearbox**

Gearbox Fluic MOBIL MOBILGEAR 600 XP 220 (--- GAL)

DIAGNOSIS

Recommendation

We recommend you service the filters on this component. We recommend an early resample to monitor this condition. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. The water content is negligible.

Fluid Condition

The AN level is acceptable for this fluid. The oil is still serviceable provided that the contaminant(s) can be reduced to acceptable levels.

| | | Samp | le Rating Tre | end | | |
|------------------------|------|-------------|---------------|------------------|------------------|----------|
| SIS REPO | ORT | | | | | ISO |
| | | | | | | |
| | | | | | | |
| | | | | | | |
| | | | | | | |
| | | | | | | |
| | | | | | | |
| | | | Jan2024 | Jun2024 | | |
| SAMPLE INFOR | | method | limit/base | current | history1 | history2 |
| | | Client Info | | WC0776484 | WC0776375 | |
| Sample Number | | Client Info | | 06 Jun 2024 | | |
| Sample Date | hrs | Client Info | | 06 Jun 2024 0 | 26 Jan 2024 0 | |
| Machine Age Oil Age | hrs | Client Info | | 0 | 0 | |
| Oil Changed | 1115 | Client Info | | N/A | N/A | |
| Sample Status | | | | ABNORMAL | ABNORMAL | |
| ÷ | | | | | | |
| WEAR METALS | | method | limit/base | e current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >200 | 9 | 20 | |
| Chromium | ppm | ASTM D5185m | >15 | 0 | 0 | |
| Nickel | ppm | ASTM D5185m | >15 | 0 | 0 | |
| Titanium | ppm | ASTM D5185m | | 0 | 0 | |
| Silver | ppm | ASTM D5185m | | 0 | 0 | |
| Aluminum | ppm | ASTM D5185m | >25 | 0 | 0 | |
| Lead | ppm | ASTM D5185m | >100 | 0 | 0 | |
| Copper | ppm | ASTM D5185m | >200 | 0 | <1 | |
| Tin | ppm | ASTM D5185m | >25 | 0 | 0 | |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 18 | 9 | |
| Barium | ppm | ASTM D5185m | | <1 | 0 | |
| Molybdenum | ppm | ASTM D5185m | | 0 | 0 | |
| Manganese | ppm | ASTM D5185m | | <1 | <1 | |
| Magnesium | ppm | ASTM D5185m | | <1 | 0 | |
| Calcium | ppm | ASTM D5185m | | 2 | 4 | |
| Phosphorus | ppm | ASTM D5185m | | 336 | 379 | |
| Zinc | ppm | ASTM D5185m | | 15 | 10 | |
| Sulfur | ppm | ASTM D5185m | | 18784 | 11734 | |
| CONTAMINANTS | S | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >50 | 6 | 14 | |
| Sodium | ppm | ASTM D5185m | | 2 | 1 | |
| Potassium | ppm | ASTM D5185m | >20 | 2 | 0 | |
| Water | % | ASTM D6304 | | 0.009 | 0.010 | |
| ppm Water | ppm | ASTM D6304 | >2000 | 95 | 102 | |
| FLUID CLEANLIN | NESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >20000 | 63674 | ▲ 98202 | |
| Particles >6µm | | ASTM D7647 | >5000 | <u> </u> | A 21893 | |
| Particles >14µm | | ASTM D7647 | >640 | 205 | 470 | |
| Particles >21µm | | ASTM D7647 | >160 | 24 | 67 | |
| Dortiolog . 00 | | ACTN D7047 | 10 | • | -1 | |

history2

1

0

0.81

24/22/16

history1



Ē

Cles

Water

Water (

OIL ANALYSIS REPORT



214

history1

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

history

historv1

NFG

NEG

227

history2

history

history2

no image

no image

4406

:1999 Cle

14

Report Id: CASASH [WUSCAR] 06204617 (Generated: 06/11/2024 19:42:45) Rev: 1

Submitted By: MARC-ANDRE HUBERT