

## **OIL ANALYSIS REPORT**

#### Sample Rating Trend

ADDITIVES

### AIR 1 (S/N 1002) Component Air Compressor

Air Compressor Fluid USPI MAX FG AIR 46 (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.


#### Fluid Condition


Additive levels indicate the addition of a different brand or type of oil. Confirmed. The AN level is acceptable for this fluid.


| SAMPLE INFORM    | ΛΑΤΙΟΝ   | method       | limit/base | current            | history1    | history2    |
|------------------|----------|--------------|------------|--------------------|-------------|-------------|
| Sample Number    |          | Client Info  |            | USPM37593          | USPM30066   | USPM27728   |
| Sample Date      |          | Client Info  |            | 31 May 2024        | 06 Feb 2024 | 17 Mar 2023 |
| Machine Age      | hrs      | Client Info  |            | 146652             | 144628      | 141702      |
| Oil Age          | hrs      | Client Info  |            | 0                  | 0           | 21486       |
| Oil Changed      |          | Client Info  |            | N/A                | N/A         | N/A         |
| Sample Status    |          |              |            | ATTENTION          | ATTENTION   | NORMAL      |
| WEAR METALS      |          | method       | limit/base | current            | history1    | history2    |
| Iron             | ppm      | ASTM D5185m  | >50        | 0                  | 1           | 0           |
| Chromium         | ppm      | ASTM D5185m  | >4         | 0                  | 0           | 0           |
| Nickel           | ppm      | ASTM D5185m  | >4         | 0                  | 0           | 0           |
| Titanium         | ppm      | ASTM D5185m  | >3         | 0                  | 0           | 0           |
| Silver           | ppm      | ASTM D5185m  | >2         | 0                  | 0           | 0           |
| Aluminum         | ppm      | ASTM D5185m  | >10        | 3                  | 0           | <1          |
| Lead             | ppm      | ASTM D5185m  | >20        | 0                  | 0           | 0           |
| Copper           | ppm      | ASTM D5185m  | >40        | 9                  | 4           | 0           |
| Tin              | ppm      | ASTM D5185m  | >5         | 0                  | <1          | 0           |
| Vanadium         | ppm      | ASTM D5185m  |            | 0                  | 0           | 0           |
| Cadmium          | ppm      | ASTM D5185m  |            | 0                  | 0           | 0           |
| ADDITIVES        |          | method       | limit/base | current            | history1    | history2    |
| Boron            | ppm      | ASTM D5185m  | 0          | 0                  | 0           | 0           |
| Barium           | ppm      | ASTM D5185m  | 0          | 4                  | 0           | 0           |
| Molybdenum       | ppm      | ASTM D5185m  | 0          | 0                  | 0           | 0           |
| Manganese        | ppm      | ASTM D5185m  |            | <1                 | <1          | 0           |
| Magnesium        | ppm      | ASTM D5185m  | 0          | 3                  | 0           | 0           |
| Calcium          | ppm      | ASTM D5185m  | 0          | 2                  | 0           | 0           |
| Phosphorus       | ppm      | ASTM D5185m  | 0          | <mark> </mark> 153 | 171         | 1           |
| Zinc             | ppm      | ASTM D5185m  | 0          | <mark> </mark> 161 | 0102        | 0           |
| Sulfur           | ppm      | ASTM D5185m  | 0          | <b>1745</b>        | 1626        | 0           |
| CONTAMINANTS     | 3        | method       | limit/base | current            | history1    | history2    |
| Silicon          | ppm      | ASTM D5185m  | >25        | <1                 | <1          | 5           |
| Sodium           | ppm      | ASTM D5185m  |            | 1                  | <1          | 0           |
| Potassium        | ppm      | ASTM D5185m  | >20        | 2                  | 1           | <1          |
| Water            | %        | ASTM D6304   |            | 0.004              | 0.003       | 0.011       |
| ppm Water        | ppm      | ASTM D6304   | >6000      | 42                 | 30          | 113.0       |
| FLUID CLEANLIN   | IESS     | method       | limit/base | current            | history1    | history2    |
| Particles >4µm   |          | ASTM D7647   |            | 94                 | 332         | 353         |
| Particles >6µm   |          | ASTM D7647   | >1300      | 50                 | 102         | 198         |
| Particles >14µm  |          | ASTM D7647   | >80        | 11                 | 15          | 56          |
| Particles >21µm  |          | ASTM D7647   |            | 3                  | 2           | 14          |
| Particles >38µm  |          | ASTM D7647   | >4         | 1                  | 0           | 0           |
| Particles >71µm  |          | ASTM D7647   |            | 0                  | 0           | 0           |
| Oil Cleanliness  |          | ISO 4406 (c) | >/17/13    | 14/13/11           | 16/14/11    | 16/15/13    |
| FLUID DEGRADA    | TION     | method       | limit/base | current            | history1    | history2    |
| Acid Number (AN) | mg KOH/g | ASTM D8045   | 0.16       | 0.43               | 0.55        | 0.08        |
|                  |          |              |            |                    |             |             |



# **OIL ANALYSIS REPORT**








lec16/1! Tah 28/1 /lav11

| VISUAL           |        | method    | limit/base | current | history1   | history2 |
|------------------|--------|-----------|------------|---------|--|----------|
| White Metal      | scalar | *Visual   | NONE       | NONE    | NONE   | NONE     |
| Yellow Metal     | scalar | *Visual   | NONE       | NONE    | NONE   | NONE     |
| Precipitate      | scalar | *Visual   | NONE       | NONE    | NONE   | NONE     |
| Silt             | scalar | *Visual   | NONE       | NONE    | NONE   | NONE     |
| Debris           | scalar | *Visual   | NONE       | NONE    | NONE   | NONE     |
| Sand/Dirt        | scalar | *Visual   | NONE       | NONE    | NONE   | NONE     |
| Appearance       | scalar | *Visual   | NORML      | NORML   | NORML  | NORML    |
| Odor             | scalar | *Visual   | NORML      | NORML   | NORML  | NORML    |
| Emulsified Water | scalar | *Visual   | >0.6       | NEG     | NEG  | NEG      |
| Free Water       | scalar | *Visual   |            | NEG     | NEG  | NEG      |
| FLUID PROPERT    | IES    | method    | limit/base | current | history1   | history2 |
| Visc @ 40°C      | cSt    | ASTM D445 | 45.8       | 47.9    | 46.6   | 46.6     |
| SAMPLE IMAGES    | 5      | method    | limit/base | current | history1   | history2 |
| Color            |        |           |            |         | Alter a transmission of the second se |          |
| Bottom           |        |           |            |         |  |          |



\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: AMEGREEAS [WUSCAR] 06204664 (Generated: 06/12/2024 18:23:27) Rev: 1

Contact/Location: Service Manager - AMEGREEAS

F: