



OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
500A
 Machine Id
1
 Component
Gearbox
 Fluid
LUBRIPLATE SFGO ULTRA 220 (20 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

| | method | limit/base | current | history1 | history2 |
|---------------|-------------|-------------|--------------------|----------|----------|
| Sample Number | Client Info | | USP0012446 | --- | --- |
| Sample Date | Client Info | | 06 Jun 2024 | --- | --- |
| Machine Age | hrs | Client Info | 3949 | --- | --- |
| Oil Age | hrs | Client Info | 1453 | --- | --- |
| Oil Changed | Client Info | | N/A | --- | --- |
| Sample Status | | | NORMAL | --- | --- |

WEAR METALS

| | method | limit/base | current | history1 | history2 |
|----------|--------|------------------|--------------|----------|----------|
| Iron | ppm | ASTM D5185m >200 | 10 | --- | --- |
| Chromium | ppm | ASTM D5185m >15 | <1 | --- | --- |
| Nickel | ppm | ASTM D5185m >15 | 0 | --- | --- |
| Titanium | ppm | ASTM D5185m | <1 | --- | --- |
| Silver | ppm | ASTM D5185m | 0 | --- | --- |
| Aluminum | ppm | ASTM D5185m >25 | 0 | --- | --- |
| Lead | ppm | ASTM D5185m >100 | 2 | --- | --- |
| Copper | ppm | ASTM D5185m >200 | 4 | --- | --- |
| Tin | ppm | ASTM D5185m >25 | 2 | --- | --- |
| Vanadium | ppm | ASTM D5185m | <1 | --- | --- |
| Cadmium | ppm | ASTM D5185m | 0 | --- | --- |

ADDITIVES

| | method | limit/base | current | history1 | history2 |
|------------|--------|-------------|--------------|----------|----------|
| Boron | ppm | ASTM D5185m | 0 | --- | --- |
| Barium | ppm | ASTM D5185m | 0 | --- | --- |
| Molybdenum | ppm | ASTM D5185m | 0 | --- | --- |
| Manganese | ppm | ASTM D5185m | <1 | --- | --- |
| Magnesium | ppm | ASTM D5185m | 0 | --- | --- |
| Calcium | ppm | ASTM D5185m | 0 | --- | --- |
| Phosphorus | ppm | ASTM D5185m | 158 | --- | --- |
| Zinc | ppm | ASTM D5185m | 10 | --- | --- |
| Sulfur | ppm | ASTM D5185m | 2273 | --- | --- |

CONTAMINANTS

| | method | limit/base | current | history1 | history2 |
|-----------|--------|------------------|--------------|----------|----------|
| Silicon | ppm | ASTM D5185m >50 | 1 | --- | --- |
| Sodium | ppm | ASTM D5185m | 1 | --- | --- |
| Potassium | ppm | ASTM D5185m >20 | <1 | --- | --- |
| Water | % | ASTM D6304 >0.2 | 0.002 | --- | --- |
| ppm Water | ppm | ASTM D6304 >2000 | 24 | --- | --- |

FLUID CLEANLINESS






| | method | limit/base | current | history1 | history2 |
|-----------------|--------------|------------|----------------|----------|----------|
| Particles >4µm | ASTM D7647 | >10000 | 232 | --- | --- |
| Particles >6µm | ASTM D7647 | >2500 | 40 | --- | --- |
| Particles >14µm | ASTM D7647 | >640 | 2 | --- | --- |
| Particles >21µm | ASTM D7647 | >160 | 0 | --- | --- |
| Particles >38µm | ASTM D7647 | >40 | 0 | --- | --- |
| Particles >71µm | ASTM D7647 | >10 | 0 | --- | --- |
| Oil Cleanliness | ISO 4406 (c) | >20/18/16 | 15/12/9 | --- | --- |

FLUID DEGRADATION

| | method | limit/base | current | history1 | history2 |
|------------------|----------|------------|--------------|----------|----------|
| Acid Number (AN) | mg KOH/g | ASTM D8045 | 0.388 | --- | --- |



OIL ANALYSIS REPORT







| VISUAL | method | limit/base | current | history1 | history2 | |
|------------------|--------|------------|---------|----------|----------|-----|
| White Metal | scalar | *Visual | NONE | NONE | --- | --- |
| Yellow Metal | scalar | *Visual | NONE | NONE | --- | --- |
| Precipitate | scalar | *Visual | NONE | NONE | --- | --- |
| Silt | scalar | *Visual | NONE | NONE | --- | --- |
| Debris | scalar | *Visual | NONE | NONE | --- | --- |
| Sand/Dirt | scalar | *Visual | NONE | NONE | --- | --- |
| Appearance | scalar | *Visual | NORML | NORML | --- | --- |
| Odor | scalar | *Visual | NORML | NORML | --- | --- |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | --- | --- |
| Free Water | scalar | *Visual | | NEG | --- | --- |

| FLUID PROPERTIES | method | limit/base | current | history1 | history2 |
|------------------|--------|---------------|---------|----------|----------|
| Visc @ 40°C | cSt | ASTM D445 222 | 207 | --- | --- |

| SAMPLE IMAGES | method | limit/base | current | history1 | history2 |
|---------------|--------|------------|---------|----------|----------|
|---------------|--------|------------|---------|----------|----------|

| | | | | | |
|--------|--|--|--|----------|----------|
| Color | | | | no image | no image |
| Bottom | | | | no image | no image |

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : USP0012446
Lab Number : 06204725
Unique Number : 11072186
Test Package : IND 2

KraftHeinz - Lowville - Plant 8322 USP
 7388 UTICA BLVD
 LOWVILLE, NY
 US 13367
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: