




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
TYSCOR LS-1 (S/N 121890)
 Component
Refrigeration Compressor
 Fluid
USPI ALT-68 SC (70 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	USP0012456	USP0004441	USP0000078
Sample Date	Client Info	01 Jun 2024	17 Dec 2023	13 Sep 2023
Machine Age	hrs	Client Info	0	0
Oil Age	hrs	Client Info	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		NORMAL	NORMAL	NORMAL

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >8	0	0
Chromium	ppm	ASTM D5185m >2	0	0
Nickel	ppm	ASTM D5185m	0	0
Titanium	ppm	ASTM D5185m	<1	0
Silver	ppm	ASTM D5185m >2	0	0
Aluminum	ppm	ASTM D5185m >3	0	0
Lead	ppm	ASTM D5185m >2	<1	0
Copper	ppm	ASTM D5185m >8	<1	<1
Tin	ppm	ASTM D5185m >4	0	0
Vanadium	ppm	ASTM D5185m	<1	0
Cadmium	ppm	ASTM D5185m	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0
Barium	ppm	ASTM D5185m	0	0
Molybdenum	ppm	ASTM D5185m	0	0
Manganese	ppm	ASTM D5185m	<1	0
Magnesium	ppm	ASTM D5185m	0	0
Calcium	ppm	ASTM D5185m	0	0
Phosphorus	ppm	ASTM D5185m	0	0
Zinc	ppm	ASTM D5185m	0	0
Sulfur	ppm	ASTM D5185m 50	0	0

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >15	2	<1
Sodium	ppm	ASTM D5185m	1	<1
Potassium	ppm	ASTM D5185m >20	<1	0
Water	%	ASTM D6304 >0.01	0.002	0.003
ppm Water	ppm	ASTM D6304 >100	18	39

FLUID CLEANLINESS






method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	153	7036	1973
Particles >6µm	ASTM D7647 >2500	47	2486	344
Particles >14µm	ASTM D7647 >320	1	162	19
Particles >21µm	ASTM D7647 >80	0	34	6
Particles >38µm	ASTM D7647 >20	0	1	0
Particles >71µm	ASTM D7647 >4	0	0	0
Oil Cleanliness	ISO 4406 (c) >--/18/15	14/13/7	20/18/15	18/16/11

FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974 0.005	0.014	0.014




OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	65.6	67.3	65.4

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : USP0012456
 Lab Number : 06204727
 Unique Number : 11072188
 Test Package : IND 2

Received : 10 Jun 2024
 Tested : 12 Jun 2024
 Diagnosed : 12 Jun 2024 - Doug Bogart

TYSON -CORYDON-USP

CORYDON, IN
 US

Contact: SERVICE MANAGER

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: