

## **OIL ANALYSIS REPORT**

Sample Rating Trend





Machine Id VOLVO A30G 752469 Component Drop Box

# GEAR OIL SAE 80W90 (--- GAL)

#### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


## Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ML0002007		
Sample Date		Client Info		04 Jun 2024		
Machine Age	hrs	Client Info		1889		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	57		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>30	6		
Lead	ppm	ASTM D5185m	>30	0		
Copper	ppm	ASTM D5185m	>30	1		
Tin		ASTM D5185m	>20	، <1		
Vanadium	ppm	ASTM D5185m	> <u>_</u> U	< 1		
	ppm					
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	160		
Barium	ppm	ASTM D5185m	200	1		
Molybdenum	ppm	ASTM D5185m	12	5		
Manganese	ppm	ASTM D5185m		3		
Magnesium	ppm	ASTM D5185m	12	3		
Calcium	ppm	ASTM D5185m	150	40		
Phosphorus	ppm	ASTM D5185m	1650	2347		
Zinc	ppm	ASTM D5185m	125	56		
Sulfur	ppm	ASTM D5185m	22500	32234		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	34		
Sodium	ppm	ASTM D5185m	>170	5		
Potassium	ppm	ASTM D5185m	>20	3		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	MODER		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual	2.01L	NEG		
3:54:13) Rev: 1	Sudiai	visual	Conta	ct/Location: DA		



# **OIL ANALYSIS REPORT**



FLUID PROPE	ERTIES me	ethod lir	nit/base curre	ent history1	history2
Visc @ 40°C	cSt AST	M D445 143	49.3		
SAMPLE IMAG	GES me	ethod lir	nit/base curre	ent history1	history2
Color			no ima	ge no image	no image
Bottom			no ima	ge no image	no image
GRAPHS					
Ferrous Alloys					
50-					
40					
Ē 30 -					
20					
10					
0			_		
Jun4/24		Jun4/24			
Non-ferrous Me	etals	~			
10 9					
8					
6					
قر 5- 4-					
3					
1-					
01424		Jun4/24	_		
		- The second sec			
Viscosity @ 40 <sup>180</sup>	°C				
160					
140 Abnormal		*****			
() 120 () 120 양 100					
80 <b>-</b> 60 <b>-</b>					
40			_		
Jun4/24		Jun4/24			
ory : WearCheck USA - No. : ML0002007 Iber : 06205124	Received Tested	e., Cary, NC : 10 Jun : 12 Jun	27513 M 2024 2024		NTMERE COUI /INCHESTER, `
mber:11072585 kage:CONST	Diagnosed	<b>d</b> : 13 Jun :	2024 - Sean Felton	Contact: D4	US 226 KOTA HARTL



\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

US 22603 Contact: DAKOTA HARTLEY dhartley@mcclung-logan.com T: F: (540)722-4441

Report Id: VOLVO4589 [WUSCAR] 06205124 (Generated: 06/14/2024 08:54:13) Rev: 1

Certificate 12367

Contact/Location: DAKOTA HARTLEY - VOLVO4589