


# **OIL ANALYSIS REPORT**

### Juli





VOLVO A30G 752469

Component
Wet Disc Brake
Fluid
VOLVO WB 102 (--- GAL)

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

#### Wear

The copper level is abnormal. All other component wear rates are normal.

## Contamination

There is a moderate amount of visible silt present in the sample.

### **Fluid Condition**


The condition of the oil is acceptable for the time in service.

AL)				Jun2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ML0002005		
Sample Date		Client Info		04 Jun 2024		
Machine Age	hrs	Client Info		1889		
Oil Age	hrs	Client Info		0		
Oil Changed	1115	Client Info		N/A		
Sample Status		Ciletit iiiio		ABNORMAL		
CONTAMINATIO	V	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	10		
Chromium	ppm	ASTM D5185m		0		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>10	<1		
Lead	ppm	ASTM D5185m	>10	0		
Copper	ppm	ASTM D5185m	>75	<u>^</u> 220		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m	>10	0		
Cadmium	ppm	ASTM D5185m		0		
	ррпп		11 11 11			
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		129		
Barium	ppm	ASTM D5185m		3		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		2		
Magnesium	ppm	ASTM D5185m		6		
Calcium	ppm	ASTM D5185m		3424		
Phosphorus	ppm	ASTM D5185m		1237		
Zinc	ppm	ASTM D5185m		1429		
Sulfur	ppm	ASTM D5185m		5032		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	15		
Sodium	ppm	ASTM D5185m		5		
Potassium	ppm	ASTM D5185m	>20	6		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	▲ MODER		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		


Contact/Location: DAKOTA HARTLEY - VOLVO4589




# **OIL ANALYSIS REPORT**



Non-ferrous Metals









Laboratory Sample No. Lab Number : 06205125

: ML0002005 Unique Number : 11072586

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

: 10 Jun 2024 Tested : 12 Jun 2024

Diagnosed : 12 Jun 2024 - Angela Borella

160 KENTMERE COURT WINCHESTER, VA

MCCLUNG-LOGAN EQUIPMENT CO - WINCHESTER

US 22603 Contact: DAKOTA HARTLEY dhartley@mcclung-logan.com

Test Package : CONST Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (540)722-4441

history2

history2

no image

no image