

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id STOCK OIL Component New (Unused) Oil

DIAGNOSIS


Recommendation


This is a baseline read-out on the submitted sample.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06205235		
Sample Date		Client Info		03 Jun 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>5	0		
Chromium	ppm	ASTM D5185m	>5	0		
Nickel	ppm	ASTM D5185m	>5	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>5	0		
Aluminum	ppm	ASTM D5185m	>5	<1		
Lead	ppm	ASTM D5185m	>5	0		
Copper	ppm	ASTM D5185m	>5	0		
Tin	ppm	ASTM D5185m	>5	0		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		<1		
Phosphorus	ppm	ASTM D5185m		514		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		3514		
CONTAMINANTS	5	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	2		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.11		



OIL ANALYSIS REPORT





			11 1. 0			
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
••			NORML	_		
Odor	scalar	*Visual	NORIVIL	NORML		
Emulsified Water	scalar	*Visual		NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
√isc @ 40°C	cSt	ASTM D445		44.16		
√isc @ 100°C	cSt	ASTM D445		7.01		
Viscosity Index (VI)	Scale	ASTM D2270		117		
			11		la facta a sud	
SAMPLE IMAGES	5	method	limit/base	current	history1	history2
Color					no image	no image
				M GENN		
Bottom					no image	no image
2						
Jun3/24			Jun3/24 -			
ul L			Πſ			
Non-ferrous Metal	s					
espiration lead						
tin						
54			24			
Jun3/24			Jun3/24			
Viscosity @ 40°C			Do 1	Acid Number		
			3/HOX			
Abnormal			<u></u> 0.1	0		
			.0 g	5-		
			0.0 HOU 0.0 Winnber 0.0 Addition 0.0 Addi			
/24				1/24		
Jun3/24			Jun3/24	Jun3/24		
-			-	-		
earCheck USA - 50				AIR SPE	CIALTY & EQUIPI	
CH06205235	Recei) Jun 2024 3 Jun 2024			B14 EAST P S
8205235			עיוועי מוווי		DI	
	Teste			than Hastor	DI	-
	Diagr	nosed :18	Jun 2024 - Jona			US 7753
1072696 ID 2 (Additional Tes htact Customer Servi	Diagr sts: FT-IR	nosed : 18 R, ICP-NewO	Jun 2024 - Jona il, KV100, Pr			EER PARK, T US 7753 AARON RIC

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

T: (281)884-2335 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Laboratory Sample No. Lab Number **Unique Number Test Package**

Contact/Location: AARON RIOS - UCAIRDEE

F: