

Area SMART OIL 6000 [32129R] HERTZ VD007148 - HORIZON SCIENTIFIC

Component Compressor

Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Moderate concentration of visible dirt/debris present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.



Sample Rating Trend




NORMAL

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UHK06205598		
Sample Date		Client Info		30 May 2024		
Machine Age	hrs	Client Info		5127		
Oil Age	hrs	Client Info		2351		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	٧	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	1		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		<1		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m	20	1		
Phosphorus	ppm	ASTM D5185m		395		
Zinc	ppm	ASTM D5185m		7		
Sulfur	ppm	ASTM D5185m		987		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1		
Sodium	ppm	ASTM D5185m		1		
Potassium	ppm	ASTM D5185m	>20	2		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.10		



OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2	
	White Metal	scalar	*Visual	NONE	NONE			
	Yellow Metal	scalar	*Visual	NONE	NONE			
	Precipitate	scalar	*Visual	NONE	NONE			
	Silt	scalar	*Visual	NONE	NONE			
	Debris	scalar	*Visual	NONE	MODER			
	Sand/Dirt	scalar	*Visual	NONE	NONE			
430/24	Appearance	scalar	*Visual	NORML	NORML			
May	Odor	scalar	*Visual	NORML	NORML			
	Emulsified Water	scalar	*Visual	>0.1	NEG			
	Free Water	scalar	*Visual		NEG			
	FLUID PROPERT	ΓIES	method	limit/base	current	history1	history2	
	Visc @ 40°C	cSt	ASTM D445	46	48.6			
	SAMPLE IMAGE	S	method	limit/base	current	history1	history2	
May30/24 +	Color					no image	no image	
	Bottom					no image	no image	
	Non-ferrous Metal			May30/24	Acid Number			
	(2.0) 40 40 40 40 40 40 40 40 40 40			May30/24 0.00 Acid Number May30/24	May30/24		POOC-W	
Laboratory	: WearCheck USA - 50						BACS INC	
Sample No. Lab Number Unique Number Test Package discuss this sample report Denotes test methods that	: 11073059 : IND 2 , contact Customer Serv are outside of the ISO 1	Teste Diagr ice at 1-8 7025 sco					SUMMERVILLE, S(US 2948 Contact: AARON LEI alee@bacsinc.cor T: (843)821-348 2) F: (843)821-339	

Contact/Location: AARON LEE - UCBACSUM