

## **OIL ANALYSIS REPORT**

Sample Rating Trend

### NORMAL

#### Machine Id

# B78 8600 EL18 BONE-IN LOIN - 1ST STG BTM (S/N 5585172) Pump

Fluid

USPI MAX FG VAC 100 (--- GAL)

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

#### Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USPM37666	USPM30182	USPM31257
Sample Date		Client Info		10 Jun 2024	27 Feb 2024	08 Nov 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ATTENTION	ATTENTION
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>90	0	0	0
Chromium	ppm	ASTM D5185m	>5	0	0	<1
Nickel	ppm	ASTM D5185m	>5	0	<1	0
Titanium	ppm	ASTM D5185m	>3	0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>7	0	<1	3
Lead	ppm	ASTM D5185m	>12	0	<1	0
Copper	ppm		>30	<1	1	<1
Tin		ASTM D5185m	>30	0	0	0
	ppm		20			
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		0	1	0
Calcium	ppm	ASTM D5185m		0	1	<1
Phosphorus	ppm	ASTM D5185m		67	213	65
Zinc	ppm	ASTM D5185m		0	<1	0
Sulfur	ppm	ASTM D5185m		227	792	660
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>60	3	2	3
Sodium	ppm	ASTM D5185m		0	<1	0
Potassium	ppm	ASTM D5185m	>20	0	1	2
Water	%	ASTM D6304	>.1	0.007	0.019	0.009
ppm Water	ppm	ASTM D6304	>1000	73	191	96.5
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	243	105	615
Particles >6µm		ASTM D7647	>1300	83	18	152
Particles >14µm		ASTM D7647	>160	9	2	14
Particles >21µm		ASTM D7647	>40	3	0	4
Particles >38µm		ASTM D7647	>10	1	0	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	15/14/10	14/11/9	16/14/11
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.093	0.25	0.23


Contact/Location: SERVICE MANAGER - FARDEN Page 1 of 2





## **OIL ANALYSIS REPORT**













VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		93.5	79.8	83.9
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color				•		
Bottom						



: 11 Jun 2024

: 14 Jun 2024

: 14 Jun 2024 - Doug Bogart



To discuss this sample report, contact Customer Service at 1-800-237-1369.

: USPM37666

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received

Diagnosed

Tested

T: (712)263-7414 F: (712)263-7314

DENISON, IA

US 51442

800 INDUSTRIAL ROAD

Contact: SERVICE MANAGER

Report Id: FARDEN [WUSCAR] 06206562 (Generated: 06/15/2024 09:49:50) Rev: 1

Contact/Location: SERVICE MANAGER - FARDEN

**SMITHFIELD - DENISON - SMIDENIOW**