


OIL ANALYSIS REPORT




Acid Number (AN)

mg KOH/g ASTM D8045 0.172



ACS-46-5 [420587] ATLAS COPCO WUX580996 - IFF Component Compressor





Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06206710	UCH05389814	UCH04959882
Sample Date		Client Info		10 Jun 2024	01 Nov 2021	25 Mar 2020
Machine Age	hrs	Client Info		2766	2596	2399
Oil Age	hrs	Client Info		40	1	53
Oil Changed		Client Info		N/A	N/A	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	0
Chromium	ppm	ASTM D5185m	>10	<1	0	0
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>25	2	0	0
Lead	ppm	ASTM D5185m	>25	0	0	0
Copper	ppm	ASTM D5185m	>50	<1	0	<1
Tin	ppm	ASTM D5185m	>15	<1	0	0
Antimony	ppm	ASTM D5185m			0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0.0	0	0	0
Barium	ppm	ASTM D5185m	0.0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	0	0
Manganese	ppm	ASTM D5185m	0	0	0	0
Magnesium	ppm	ASTM D5185m	0.0	<1	0	0
Calcium	ppm	ASTM D5185m	0.0	0	0	0
Phosphorus	ppm	ASTM D5185m	966	185	185	138
Zinc	ppm	ASTM D5185m	0	32	0	69
Sulfur	ppm	ASTM D5185m	1309	1916	1394	378
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	0	<1
Sodium	ppm	ASTM D5185m		0	0	<1
Potassium	ppm	ASTM D5185m	>20	<1	0	4
FLUID DEGRADA	TION	method	limit/base	current	history1	history2

0.055


0.105

0.164



38

OIL ANALYSIS REPORT





VIOLIAI			12 - 25 //		111	1111
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	39.9	41.9	40.5	44.2
SAMPLE IMAGES		method	limit/base	current	history1	history2




Color

Bottom











Certificate 12367

Report Id: UCAIRCAR [WUSCAR] 06206710 (Generated: 06/15/2024 08:10:13) Rev: 1

Laboratory Sample No. Unique Number : 11074171 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Lab Number : 06206710

: UCH06206710

Received : 11 Jun 2024 **Tested**

: 13 Jun 2024 Diagnosed : 13 Jun 2024 - Sean Felton

AIRMATIC COMPRESSOR SYSTEMS

700 WASHINGTON AVE CARLSTADT, NJ

US 07072

T: (800)864-7621

Contact: ELVIN DIAZ ediaz@airmaticcompressor.com;canastasio@wearcheckusa.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

F: (201)342-6241

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)