OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
TS03-08
Component
Hydraulic System
Fluid
DURACLEAN ISO 46 (330 GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Particle Filter (Magn: 200 x)



SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PH0001190**	PH0001188	PH0001186
Sample Date		Client Info		**03 Jun 2024**	03 Apr 2024	07 Feb 2024
Machine Age	hrs	Client Info		**0**	0	0
Oil Age	hrs	Client Info		**0**	0	0
Oil Changed		Client Info		**N/A**	N/A	N/A
Sample Status				**NORMAL**	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.05	**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	**<1**	0	0
Chromium	ppm	ASTM D5185m	>20	**<1**	0	0
Nickel	ppm	ASTM D5185m	>20	**0**	0	0
Titanium	ppm	ASTM D5185m		**<1**	0	0
Silver	ppm	ASTM D5185m		**0**	0	0
Aluminum	ppm	ASTM D5185m	>20	**2**	0	0
Lead	ppm	ASTM D5185m	>20	**<1**	0	0
Copper	ppm	ASTM D5185m	>20	**20**	16	17
Tin	ppm	ASTM D5185m	>20	**<1**	0	<1
Vanadium	ppm	ASTM D5185m		**0**	0	0
Cadmium	ppm	ASTM D5185m		**<1**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		**0**	0	0
Barium	ppm	ASTM D5185m		**0**	0	0
Molybdenum	ppm	ASTM D5185m		**0**	0	0
Manganese	ppm	ASTM D5185m		**0**	0	<1
Magnesium	ppm	ASTM D5185m		**<1**	0	0
Calcium	ppm	ASTM D5185m		**18**	24	19
Phosphorus	ppm	ASTM D5185m		**368**	408	396
Zinc	ppm	ASTM D5185m		**559**	535	523
Sulfur	ppm	ASTM D5185m		**1052**	1299	1091

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	**1**	0	<1
Sodium	ppm	ASTM D5185m		**0**	1	<1
Potassium	ppm	ASTM D5185m	>20	**1**	0	0

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	**1579**	2164	1082
Particles >6µm		ASTM D7647	>2500	**300**	293	222
Particles >14µm		ASTM D7647	>320	**9**	19	13
Particles >21µm		ASTM D7647	>80	**1**	5	4
Particles >38µm		ASTM D7647	>20	**0**	0	0
Particles >71µm		ASTM D7647	>4	**0**	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	**18/15/10**	18/15/11	17/15/11

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		**0.55**	0.59	0.51

OIL ANALYSIS REPORT

Particle Count



Particle Trend



Viscosity @ 40°C



Particle Trend



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		**46.9**	43.1	42.9

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					
PrtFilter					



GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Particle Filter (Magn: 200 x)



Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PH0001190
Lab Number : 06207761
Unique Number : 11075222
Test Package : PLANT (Additional Tests: PrtFilter)

Received : 12 Jun 2024
Tested : 18 Jun 2024
Diagnosed : 18 Jun 2024 - Jonathan Hester

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

PARKER HANNIFIN CORPORATION
221 HELICOPTER CIR
CORONA, CA
US 92878
Contact: ALEX ALVAREZ
alex.alvarez@parker.com
T: (951)475-6106
F: