




OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id
KAESER AS 30 4731136 (S/N 1165)
 Component
Compressor
 Fluid
KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		KCPA018490	KCPA007767	KCP52708
Sample Date	Client Info		23 May 2024	10 Oct 2023	20 Apr 2023
Machine Age	hrs	Client Info	44287	40693	38934
Oil Age	hrs	Client Info	3000	0	0
Oil Changed	Client Info		Changed	N/A	Changed
Sample Status			ABNORMAL	ABNORMAL	ABNORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	<1	<1	<1
Chromium	ppm	ASTM D5185m >10	<1	<1	0
Nickel	ppm	ASTM D5185m >3	0	0	0
Titanium	ppm	ASTM D5185m >3	<1	0	0
Silver	ppm	ASTM D5185m >2	0	0	0
Aluminum	ppm	ASTM D5185m >10	2	<1	0
Lead	ppm	ASTM D5185m >10	<1	0	0
Copper	ppm	ASTM D5185m >50	1	3	<1
Tin	ppm	ASTM D5185m >10	<1	<1	0
Antimony	ppm	ASTM D5185m	---	---	---
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	0	0	0
Barium	ppm	ASTM D5185m 90	41	37	<1
Molybdenum	ppm	ASTM D5185m 0	0	0	0
Manganese	ppm	ASTM D5185m	0	<1	0
Magnesium	ppm	ASTM D5185m 100	81	60	13
Calcium	ppm	ASTM D5185m 0	0	1	0
Phosphorus	ppm	ASTM D5185m 0	0	42	10
Zinc	ppm	ASTM D5185m 0	2	30	17
Sulfur	ppm	ASTM D5185m 23500	21091	26446	4965

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	<1	2	4
Sodium	ppm	ASTM D5185m	29	33	9
Potassium	ppm	ASTM D5185m >20	5	3	2
Water	%	ASTM D6304 >0.05	0.038	0.028	0.027
ppm Water	ppm	ASTM D6304 >500	383	281.9	275.3






FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		8747	73115	21139
Particles >6µm	ASTM D7647	>1300	▲ 2980	▲ 24072	▲ 6117
Particles >14µm	ASTM D7647	>80	▲ 234	▲ 1652	▲ 618
Particles >21µm	ASTM D7647	>20	▲ 47	▲ 442	▲ 130
Particles >38µm	ASTM D7647	>4	1	▲ 18	▲ 9
Particles >71µm	ASTM D7647	>3	0	1	0
Oil Cleanliness	ISO 4406 (c)	>--/17/13	▲ 20/19/15	▲ 23/22/18	▲ 22/20/16

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045 1.0	0.38	0.31	0.23

OIL ANALYSIS REPORT








PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445 45	48.0	48.5	46.6

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KCPA018490 **Received** : 12 Jun 2024
Lab Number : 06207800 **Tested** : 13 Jun 2024
Unique Number : 11075261 **Diagnosed** : 14 Jun 2024 - Don Baldrige
Test Package : IND 2 (Additional Tests: KF, PrtCount)

BURLINGTON COAT FACTORY
 570 E MILL ST
 SAN BERNARDINO, CA
 US 92403
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)