

OIL ANALYSIS REPORT

Area East Molding 518 (S/N 61024486)

Hydraulic System Fluid AW HYDRAULIC OIL ISO 46 (265 GAL)

DIAGNOSIS

Recommendation

We recommend you service the filters on this component. Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear


All component wear rates are normal.

Contamination

There is a light amount of silt (particulates < 14 microns in size) present in the oil. The water content is negligible.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		RP0043251	RP0035823	RP0029223
Sample Date		Client Info		08 Jun 2024	28 Nov 2023	03 May 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ATTENTION	ATTENTION	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	4	2	3
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	<1	0	0
Lead	ppm	ASTM D5185m	>20	6	8	11
Copper	ppm	ASTM D5185m		10	11	11
Tin	ppm	ASTM D5185m	>20	0	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	1- 1-	method	limit/base	current	history1	history2
Boron	nnm	ASTM D5185m	5	0	0	0
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	5	1	0	1
	ppm		C	۱ <1	0	
Manganese	ppm	ASTM D5185m	25	3	1	<1 7
Magnesium	ppm	ASTM D5185m		-	58	
Calcium	ppm	ASTM D5185m	200	56		62
Phosphorus	ppm	ASTM D5185m	300	345	355	355
Zinc	ppm	ASTM D5185m	370	391	407	423
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1	<1	<1
Sodium	ppm	ASTM D5185m		4	3	0
Potassium	ppm	ASTM D5185m	>20	2	0	2
Water	%	ASTM D6304	>0.05	0.008	0.004	0.003
ppm Water	ppm	ASTM D6304	>500	83	48	26.9
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	6606	5065	519
Particles >6µm		ASTM D7647		<mark> </mark> 1624	642	104
Particles >14µm		ASTM D7647		111	159	5
Particles >21µm		ASTM D7647	>40	25	40	1
Particles >38µm		ASTM D7647	>10	1	2	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	0/18/14	20/18/14	16/14/10
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.39	0.44	0.37





OIL ANALYSIS REPORT













VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	44.0	43.8	44.1
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
Color				a.	•	

Bottom





To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: JOHHOL [WUSCAR] 06208281 (Generated: 06/15/2024 08:54:17) Rev: 1

Certificate 12367

Contact/Location: JEFF HARRIS - JOHHOL

jeffrey.harris@yanfeng.com

Page 2 of 2

T: (616)915-4443

F: (616)394-1725