


# **OIL ANALYSIS REPORT**

Area LSS-9300-5 **QUINCY 98086H - PACTIV** 

Component



## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06208850	UCH06101057	
Sample Date		Client Info		12 Jun 2024	07 Feb 2024	
Machine Age	hrs	Client Info		0	15886	
Oil Age	hrs	Client Info		0	4864	
Oil Changed		Client Info		N/A	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINATIO	V	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	
Chromium	ppm	ASTM D5185m	>10	0	<1	
Nickel	ppm	ASTM D5185m		0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	0	2	
Lead	ppm	ASTM D5185m	>25	0	0	
Copper	ppm	ASTM D5185m	>50	0	<1	
Tin	ppm	ASTM D5185m	>15	<1	0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m		0	8	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		0	0	
Magnesium	ppm	ASTM D5185m		0	<1	
Calcium	ppm	ASTM D5185m		0	0	
Phosphorus	ppm	ASTM D5185m		85	138	
Zinc	ppm	ASTM D5185m		0	0	
Sulfur	ppm	ASTM D5185m		221	447	
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3	<1	
Sodium	ppm	ASTM D5185m		0	0	
Potassium	ppm	ASTM D5185m	>20	0	1	
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.64	0.57	



42

## **OIL ANALYSIS REPORT**




VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
<b>Emulsified Water</b>	scalar	*Visual	>0.1	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPERT	TIES	method	limit/base	current	history1	history2

I LOID I NOI LIN	TILO	memou		HISTOLAL	HISTOLYZ
visc @ 40°C	cSt	ASTM D445	52.2	50.0	


Color	ACA, Bu, Bu, Bu, Bu, Bu, Bu, Bu, Bu, Bu, Bu	no image
Bottom		no image


### **GRAPHS**

SAMPLE IMAGES



	1	Ion-ferrous Metals	
		copper	
_	6 -	MARAAAAAAA lead	
ppm	4		
	2-		
	0 1	Jun/2/24	









Certificate 12367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Lab Number : 06208850 Unique Number : 11076311

: UCH06208850

Received : 13 Jun 2024 Tested Diagnosed

: 14 Jun 2024 : 14 Jun 2024 - Wes Davis

**LEWIS SYSTEMS & SERVICE CO INC** 9300 STOCKPORT PL

CHARLOTTE, NC US 28273 Contact: SCOTT KEE

skee@lewissystemsinc.com T: (704)588-2299

Test Package : IND 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: UCLEWCHA [WUSCAR] 06208850 (Generated: 06/14/2024 15:36:37) Rev: 1

Contact/Location: SCOTT KEE - UCLEWCHA