

OIL ANALYSIS REPORT

Sample Rating Trend





[W/O 10897] VOLVO A45G 352606 Component Front Axle

Fluid VOLVO SUPER GEAR OIL 75W-80-GO102 (8 GAL)

DIAGNOOIO

Recommendation

The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.

Area

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

Confirm oil type. The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ML0002260		
Sample Date		Client Info		04 Jun 2024		
Machine Age	hrs	Client Info		4115		
Oil Age	hrs	Client Info		4115		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>900	218		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>30	0		
Lead	ppm	ASTM D5185m	>50	0		
Copper	ppm	ASTM D5185m	>150	6		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		228		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		1		
Manganese	ppm	ASTM D5185m		7		
Magnesium	ppm	ASTM D5185m		2		
Calcium	ppm	ASTM D5185m		162		
Phosphorus	ppm	ASTM D5185m		1009		
Zinc	ppm	ASTM D5185m		89		
Sulfur	ppm	ASTM D5185m		27078		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	6		
Sodium	ppm	ASTM D5185m		1		
Potassium	ppm	ASTM D5185m	>20	1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	MODER		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		



OIL ANALYSIS REPORT



FLUID PROPER		method	limit/base	current	history1	history2
/isc @ 40°C	cSt	ASTM D445		136		
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						
Ferrous Alloys						
tion tion tion tion tion tion tion tion tion tion			Jun4/24			
Non-ferrous Meta	ls					
copper lead						
5 -						
9						
2						
Jun4/24		*******	Jun4/24			
Viscosity @ 40°C						
)						
, Abnormal						
Abnormal						
). 						
Abnormal						
Jun4/24			Jun4/24 -			



Submitted By: DELANO GREGORY Page 2 of 2