




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area

[W120103]

Machine Id

COD GOODWIN PUMP 360094

Component

Diesel Engine

Fluid

SHELL 15W40 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0797286	WC0663203	WC0616154
Sample Date	Client Info		27 Oct 2023	26 Oct 2022	22 Oct 2021
Machine Age	hrs	Client Info	0	328	294
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		N/A	Not Changd	Not Changd
Sample Status			NORMAL	NORMAL	ATTENTION

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>200	10	6	12
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>2	<1	<1	1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>30	2	1	2
Lead	ppm	ASTM D5185m	>30	2	<1	6
Copper	ppm	ASTM D5185m	>30	2	1	5
Tin	ppm	ASTM D5185m	>15	4	2	5
Antimony	ppm	ASTM D5185m		---	---	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	<1

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		91	93	52
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		23	22	7
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		450	451	322
Calcium	ppm	ASTM D5185m		1603	1658	2011
Phosphorus	ppm	ASTM D5185m		899	1005	748
Zinc	ppm	ASTM D5185m		1133	1162	1046
Sulfur	ppm	ASTM D5185m		3800	4469	3621

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>30	10	8	12
Sodium	ppm	ASTM D5185m	>150	<1	0	3
Potassium	ppm	ASTM D5185m	>20	3	0	<1

INFRA-RED




	method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844	>3	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	6.9	7.1	6.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.9	19.4	17.3

FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.3	13.2	12.7
Base Number (BN)	mg KOH/g	ASTM D2896		9.0	10.1	---











OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	13.0	13.2	17.9

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0797286 **Received** : 14 Jun 2024
Lab Number : 06209706 **Tested** : 15 Jun 2024
Unique Number : 11077167 **Diagnosed** : 15 Jun 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

NATIONAL POWER CORP
 4541 PRESLYN DR
 RALEIGH, NC
 US 27616
 Contact: Brandon Daniels
 Brandon.Daniels@natpow.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (919)790-9714