

## **OIL ANALYSIS REPORT**

#### Sample Rating Trend

## NORMAL

## Area MP-135 [10024289333] B36983 - AFECO HYDR POWER UNIT NORTH HAM CONDITIONER Component

Hydraulic System

PETRO CANADA PURITY FG AW HYDRAULIC 46 (30 GAL)

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

## Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	<b>IATION</b>	method	limit/base	current	history1	history2		
Sample Number		Client Info		WC0930455	WC0907986	WC0894886		
Sample Date		Client Info		10 Jun 2024	04 Apr 2024	15 Feb 2024		
Machine Age	days	Client Info		0	0	0		
Dil Age	days	Client Info		0	0	0		
Dil Changed		Client Info		N/A	N/A	Not Changd		
Sample Status				NORMAL	NORMAL	NORMAL		
CONTAMINATION	٨	method	limit/base	current	history1	history2		
Water		WC Method	>0.05	NEG	NEG	NEG		
WEAR METALS		method	limit/base	current	history1	history2		
ron	ppm	ASTM D5185m	>20	<1	<1	2		
Chromium	ppm	ASTM D5185m	>20	0	0	0		
lickel	ppm	ASTM D5185m	>20	0	0	0		
Titanium	ppm	ASTM D5185m		<1	0	0		
Silver	ppm	ASTM D5185m		0	0	0		
Aluminum	ppm	ASTM D5185m	>20	0	0	0		
ead	ppm	ASTM D5185m	>20	<1	0	0		
Copper	ppm	ASTM D5185m	>20	0	0	0		
īn	ppm	ASTM D5185m	>20	0	0	0		
/anadium	ppm	ASTM D5185m		<1	0	0		
Cadmium	ppm	ASTM D5185m		0	0	0		
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m		0	0	0		
Barium	ppm	ASTM D5185m		0	0	0		
lolybdenum	ppm	ASTM D5185m		0	0	0		
<i>M</i> anganese	ppm	ASTM D5185m		0	0	0		
lagnesium	ppm	ASTM D5185m		0	0	0		
Calcium	ppm	ASTM D5185m		0	0	0		
hosphorus	ppm	ASTM D5185m		434	421	463		
linc	ppm	ASTM D5185m		5	0	0		
Sulfur	ppm	ASTM D5185m		628	516	542		
CONTAMINANTS		method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>15	3	3	3		
Sodium	ppm	ASTM D5185m		1	<1	1		
Potassium	ppm	ASTM D5185m	>20	<1	0	0		
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2		
Particles >4µm		ASTM D7647	>10000	2323	4319	846		
Particles >6µm		ASTM D7647	>2500	544	1379	285		
Particles >14µm		ASTM D7647	>320	67	167	24		
Particles >21µm		ASTM D7647	>80	24	57	6		
Particles >38µm		ASTM D7647	>20	2	3	0		
Particles >71µm		ASTM D7647	>4	0	0	0		
Dil Cleanliness		ISO 4406 (c)	>20/18/15	18/16/13	19/18/15	17/15/12		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2		
Acid Number (AN)	mg KOH/g	ASTM D8045	0.26	0.22	0.25	0.25		
:08:25) Rev: 1				Contact/Loc	Contact/Location: RYAN LOWE - HORAUS			


Report Id: HORAUS [WUSCAR] 06210049 (Generated: 06/17/2024 11:08:25) Rev: 1


Contact/Location: RYAN LOWE - HORAUS Page 1 of 2




# **OIL ANALYSIS REPORT**











VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	45.36	45.9	45.9	49.2
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
Color						
Bottom						





Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: HORAUS [WUSCAR] 06210049 (Generated: 06/17/2024 11:08:25) Rev: 1

Contact/Location: RYAN LOWE - HORAUS

Page 2 of 2