

## **OIL ANALYSIS REPORT**

Area ACAS 115 CHICAGO PNEUMATIC API171042

Component Compressor

#### DIAGNOSIS

#### Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

### Wear


All component wear rates are normal.

## Contamination

Moderate concentration of visible dirt/debris present in the oil.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.





NORMAL


SAMPLE INFORM	NATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06210238		
Sample Date		Client Info		20 May 2024		
Machine Age	hrs	Client Info		21820		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	3		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	1		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	3		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		<1		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		1		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		0		
Phosphorus	ppm	ASTM D5185m		43		
Zinc	ppm	ASTM D5185m		191		
Sulfur	ppm	ASTM D5185m		34		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	13		
Sodium	ppm	ASTM D5185m		5		
Potassium	ppm	ASTM D5185m	>20	4		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.23		

Sample Rating Trend



# **OIL ANALYSIS REPORT**

VISUAI



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	MODER		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
0/24 -	Appearance	scalar	*Visual	NORML	NORML		
May20/24	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
	Free Water	scalar	*Visual		NEG		
				line it //s e e e		la la tanını d	histow.0
	FLUID PROPERT		method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		47.6		
	SAMPLE IMAGES	S	method	limit/base	current	history1	history2
Mar20/24 +	Color					no image	no image
	Bottom					no image	no image
	Non-ferrous Metal			May20124 May20124 0.0 0.1 0.0 0.1 0.0 0.1 0.0 0.1 0.0 0.1 0.	Acid Number		
Laboratory Sample No. Lab Number Unique Number Test Package	: 11083102	1 Madiso Recei Teste Diagr	ived : 14 d : 18	r, NC 27513 Jun 2024 Jun 2024 - Se	ADVANCED		SOLUTIONS (ACA 0 RD BLDG 2 TOMBALL, T US 7737 1: JIM SUARE

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: JIM SUAREZ - UCADVTOM

F: