

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area AEON 4000 GARDNER DENVER D210882

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UHC06210283	UCH05471482	
Sample Date		Client Info		06 Jun 2024	10 Feb 2022	
Machine Age	hrs	Client Info		9634	1916	
Oil Age	hrs	Client Info		4931	1916	
Oil Changed		Client Info		Changed	Not Changd	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	
Chromium	ppm	ASTM D5185m	>10	0	0	
Nickel	ppm	ASTM D5185m		0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	0	0	
Lead	ppm	ASTM D5185m	>25	0	0	
Copper	ppm	ASTM D5185m	>50	3	1	
Tin	ppm	ASTM D5185m	>15	0	0	
Antimony	ppm	ASTM D5185m			0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		2	0	
Barium	ppm	ASTM D5185m	20	0	0	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		0	0	
Magnesium	ppm	ASTM D5185m		0	0	
Calcium	ppm	ASTM D5185m	20	0	0	
Phosphorus	ppm	ASTM D5185m	320	0	3	
Zinc	ppm	ASTM D5185m	20	0	0	
Sulfur	ppm	ASTM D5185m	1400	3328	2707	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	<1	
Sodium	ppm	ASTM D5185m		0	0	
Potassium	ppm	ASTM D5185m	>20	0	0	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.09	0.06	





OIL ANALYSIS REPORT

VISUAL



	VISUAL		method	limit/base			,
	White Metal	scalar	*Visual	NONE	LIGHT	MODER	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	LIGHT	MODER	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Jun6/24	Appearance	scalar	*Visual	NORML	NORML	NORML	
Lu L	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
	Free Water	scalar	*Visual		NEG	NEG	
	FLUID PROPERT		method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	46.6	46.3	45.6	THStory 2
	-						
	SAMPLE IMAGES	5	method	limit/base	current	history1	history2
+ to be the top to be top top to be top	Color				. 0		no image
	Bottom						no image
	Non-ferrous Metal	s		Acid Number (mg KOH(g) 000 (mg KOH(g)	Acid Numbe	9 r	
Laboratory Sample No. Lab Number Unique Number	* WearCheck USA - 50 : UHC06210283 : 06210283	Recei Teste	on Ave., Cary, NC 27513 eived : 14 Jun 2024			ATLANTA AIR COMPRESSO 123 MERCHANTS PARK D HOSCHTON, G US 3054 Contact: Derik Bra	

Contact/Location: Derik Bray - UCATLHOS